

STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION  
**PAVEMENT EVALUATION CORING AND CONDITION DATA**

Cored by: Terracon Consultants, inc. Date: 09/08/21 Page 1 of 2 Typical Section No.: \_\_\_\_\_

W.P.I. No.:		Name: sr 568 Veteran's Expressway			Lanes: 4	
Fin. Proj. ID: 445885-1-52-01		From: MM 0			Shoulder Type and Condition:	
F.A. Proj. No.:		To: MM 3			Inside: Asphalt Paved	
County: Hillsborough	SR No.: 568	Beg MP: 0	End MP: 3	Lgth: 3	Outside: Asphalt Paved	
Median Curbed (Y/N): N		Lawn		Other: N/A		Curb & Gutter (Y/N): N

Core No.	Mile Post or Sta. No.	Lane	W P a t h	Pavement Layer (in.)					Core Lgth (in.)	Base		Crack				P C o m n d	D R e p t h (in.)	C S R l o o s e (%)	Comments
				Top	S	S	S	S		LR (in.)	D e p t h (in.)	T y p e	C l a s s	E x t e n t					
1	0.5	R1	LT	0.7	0.8	1.8			3.3	10.5					F			Delam at 1.5 inches	
2	0.7	R2	RT	0.5	1.0	1.6			3.1	11.0		3.1	B	III	L	F		Crack is 412 ft long	
3	0.9	OR			1.0	1.4	1.4		3.8	5.0						G			
4	1.0	R1	RT	1.0	0.8	2.8	2.6		7.2	9.5						P			
5	1.1	R2	LT	0.5	1.0	1.7			3.2	11.0						F			
6	1.3	IR			0.9	0.9			1.8	8.0									
7	2.1	R1	LT	1.0	1.0	1.1			3.1	11.0						F			
8	2.4	R2	LT	1.1	1.5	1.4			4.0	10.0						P			
9	2.5	R1	RT	1.2	1.0	1.0	1.0		4.2	10.0						F			
10	2.6	R2	RT	1.0	1.0	1.0	1.1		4.1	10.5						F			
11	2.6	OR			1.8				1.8	7.0									
12	2.7	L2	RT	0.7	1.1	1.7			3.5	11.0						F			
13	2.5	OR			0.6	1.3			1.9	6.0						G			
14	2.1	L1	RT	1.1	0.9	0.9			2.9	11.0						F			
15	1.9	L2	LT	1.0	1.0	1.3			3.3	11.0						F		Severe Ravelling	
16	1.5	L2	RT	1.1	0.9	1.4			3.4	10.5		3.4	A	III	S	P		Crack is 606 ft long	
17	1.4	L1	RT	0.6	1.5	1.2			3.3	11.5		3.3	A	III	S	P		Crack is 300 ft long	

**Layer Codes**

ARMI	Asphalt Rubber Membrane Interlayer
BIND	Asphalt Binder Course
BRCK	Brick Pavers
CONC	Portland Cement Concrete
CRL	Crack Relief Layer
FAB	Pavement Overlay Fabric
FC	Friction Course
FC1	Friction Course 1
FC2	Friction Course 2
FC3	Friction Course 3
FC4	Friction Course 4
FC5	Friction Course 5
FC6	Friction Course 6
F95	Friction Course 9.5 mm
F125	Friction Course 12.5 mm
S	Type S Asphaltic Concrete
SAHM	Sand Asphalt Hot Mix
SP1C	9.5mm Coarse Graded
SP1F	9.5mm Fine Graded

18	1.3	OL			1.3	1.3				2.6	5.5						G			
19	0.8	L2	LT	0.8	0.8	1.6	1.3			4.5	10.0		0.8	A	III	L	F			Crack only in FC, 1540 ft long
20	0.6	L1	RT	1.0	1.0	1.5				3.5	10.5						F			
21	0.6	IL			0.9	1.2				2.1	2.0									
22	0.9	L2	LT	0.8	1.5	0.9	1.8	1.9		6.9	10.0						F			Exit 0 Ramp 10471001
23	0.1	OL			1.3	1.0				2.3	12.0						G			Exit 0 Ramp 10471001
24	0.1	L1		0.7	1.3	1.0	1.5			4.5	11.0						G			Exit 0 Ramp 10471001
25	2.9	L1	LT	1.3	1.9	1.2				4.4	10.0						G			
26	0.1	L2	RT	0.7	1.3					2.0	12.0						G			Exit 3 Ramp 10471010
27	0.1	OL			1.1	1.3				2.4	2.0						G			Exit 3 Ramp 10471010

- SP2C 12.5mm Coarse Graded
- SP2F 12.5mm Fine Graded
- SP3C 19.0mm Coarse Graded
- SP3F 19.0mm Fine Graded
- ST Surface Treatment
- S1 Type S-I Asphaltic Concrete
- S2 Type S-II Asphaltic Concrete
- S3 Type S-III Asphaltic Concrete
- T1 Type I Asphaltic Concrete
- T2 Type II Asphaltic Concrete
- T3 Type III Asphaltic Concrete
- UNIM Unimproved Surface
- UNKW Unknown
- WC Wearing Course
- WC1 Wearing Course 1
- WC2 Wearing Course 2
- WC3 Wearing Course 3
- WC4 Wearing Course 4
- WC5 Wearing Course 5
- WC6 Wearing Course 6
- WC7 Wearing Course 7
- WC8 Wearing Course 8