

## Equipment Checklist

### ASTM C 1611 Slump Flow of Self-Consolidating Concrete

		P	F	N/A
<b>Item</b>				
1.	<b>Mold</b> – Conforming to the requirements of ASTM C-143.			
2.	<b>Base Plate</b> – A nonabsorbent, smooth, rigid plate having a minimum diameter of 36 inches (915 mm).			
3.	<b>Strike-off Bar</b> – Conforming to the requirements of ASTM C-173 or ASTM C-231.			
4.	<b>Measuring Device</b> – A ruler, metal roll-up measuring tape, or similar rigid or semi-rigid measuring instrument marked in increments of ¼ inch (5 mm) or less.			
5.	<b>Sample Receptacle</b> – A pan or wheelbarrow that is water-tight, has a nonabsorbent surface, and is large enough to allow both remixing of the entire sample and retain a volume of SCC sufficient to fill the mold.			
6.	<b>Other Tools</b> – Items such as shovels and scoops capable of remixing the SCC in the sample receptacle, filling the pouring vessel, or both.			

**Remarks:**

Date: \_\_\_\_\_ Technician: \_\_\_\_\_ IA Observer: \_\_\_\_\_

Technician's E-mail Address: \_\_\_\_\_

Employer's/Supervisor's E-mail Address: \_\_\_\_\_