

**SECTION 955**  
**TIMBER TREATMENT**  
**(INCLUDING TREATING MATERIALS)**

**955-1 General.**

The work specified in this Section is the treating of structural timber, timber piling and timber posts. The method of treatment for all such timber materials shall be in accordance with AASHTO M 133, or American Wood Protection Association (AWPA) Use Category System (UCS) - U1, with the exceptions and additions as specified herein.

**955-2 Preservative.**

**955-2.1 Salt or Brackish Water Use:** The treating of Southern Yellow Pine (SYP) lumber or timber for use in salt or brackish water environments shall be done with Chromated Copper Arsenate (CCA) in accordance with AWPA U1.

**955-2.2 Above Ground or Ground Contact and Fresh Water Immersion Use:** The treating of SYP lumber and timber for above ground or ground contact and fresh water immersion applications, shall be done with, Ammoniacal Copper Zinc Arsenate (ACZA), Copper Azole (CA), Micronized Copper Azole (MCA), Alkaline Copper Quat (ACQ), Micronized Copper Quat (MCQ), or CCA, with the following exceptions:

Treatment of the wood products of the pedestrian bridges, wood rails at buildings or rest areas, and fence posts shall be done either with CA, MCA, or ACQ.

**955-3 Process.**

All timber and lumber items shall be treated in accordance with AWPA T1.

**955-4 Requirements for Preservative Materials.**

ACQ, CCA, CA, MCA and ACZA shall be in accordance with the appropriate AWPA P Standard. MCA shall be in accordance with the appropriate ICC Evaluation Service (ICC-ES) ESR Report.

**955-5 Requirements for Retention.**

**955-5.1 Piling:** All pilings shall be treated in accordance with AWPA U1.

**955-5.2 Structural Timber and Sheet Piles:** All structural timber and sheet piles shall be treated in accordance with AWPA U1.

**955-5.3 Posts:** All posts shall be treated in accordance with AWPA U1.

**955-5.4 Determination of Retention:** Retention shall be determined by assay performed and certified by the treating company in accordance with the applicable AWPA standards.

**955-6 Penetration Requirements.**

The penetration of the treatment shall be in accordance with AWPA T1.

**955-7 Handling Waterborne Preservative Treated Piling.**

In handling of piles that have been treated with chromated copper arsenate (CCA) or ammoniacal copper zinc arsenate (ACZA), cable slings shall be used. Mechanical grabbers or pointed tools shall not be permitted. Rough or careless handling shall be avoided at all times.

**955-8 Identification of Treating Plants for Round Piling.**

The treating plant shall brand, or place a distinctive permanent mark, on each round pile, approximately 6 feet from the butt end, such that the plant responsible for the treatment can be readily determined at any time during the service life of the piling.