

ORINATION FORM

Proposed Revisions to the Specifications

(Please provide all information - incomplete forms will be returned)

Date:

Office:

Originator:

Specification Section:

Telephone:

Article/Subarticle:

email:

Will the proposed revision require changes to:

Publication	Yes	No	Office Staff Contacted
Standard Plans Index			
Traffic Engineering Manual			
FDOT Design Manual			
Construction Project Administration Manual			
Basis of Estimate/Pay Items			
Structures Design Guidelines			
Approved Product List			
Materials Manual			

Will this revision necessitate any of the following:

Design Bulletin

Construction Bulletin

Estimates Bulletin

Materials Bulletin

Are all references to external publications current?

Yes

No

If not, what references need to be updated? (Please include changes in the redline document.)

Why does the existing language need to be changed?

Summary of the changes:

Are these changes applicable to all Department jobs?

Yes

No

If not, what are the restrictions?

Contact the State Specifications Office for assistance in completing this form.

Dan Hurtado 850-414-4130 dan.hurtado@dot.state.fl.us Debbie Toole 850-414-4114 deborah.toole@dot.state.fl.us

Rebecca Frimmel 850-414-4155 rebecca.frimmel@dot.state.fl.us



Florida Department of Transportation

RON DESANTIS
GOVERNOR

605 Suwannee Street
Tallahassee, FL 32399-0450

KEVIN J. THIBAUT
SECRETARY

MEMORANDUM

DATE: May 2, 2019
TO: Specification Review Distribution List
FROM: Dan Hurtado, P.E., State Specifications Engineer
SUBJECT: Proposed Specification: **9290000 Pozzolans and Slag.**

In accordance with Specification Development Procedures, we are sending you a copy of a proposed specification change.

This change was proposed by Jose Armenteros of the State Materials Office (SMO) to modify the language.

Please share this proposal with others within your responsibility. Review comments are due within four weeks and should be sent to Mail Station 75 or online at

<http://www2.dot.state.fl.us/ProgramManagement/Development/IndustryReview.aspx> .

Comments received after **May 30, 2019**, may not be considered. Your input is encouraged.

DH/dt
Attachment

POZZOLANS AND SLAG.**(REV 4-16-19)**

SECTION 929 is deleted and the following substituted:

SECTION 929**~~POZZOLANS AND SLAG~~ SUPPLEMENTARY CEMENTITIOUS MATERIALS****929-1 Basis for Source Approval.**

929-1.1 General: The cementitious materials supplier shall submit the proposed Quality Control (QC) Plan, certified test reports from an approved independent laboratory acceptable to the State Materials Office (SMO), and a sample of the material for Department verification. The Quality Control Program of a cementitious materials supplier shall conform to Section 105. Continuance of Department qualifications is subject to satisfactory results from periodic verification evaluations. A verification sample may be taken at the manufacturer's plant, distribution facility or at the concrete producer's plant.

Upon review of the QC Plan and satisfactory verification of the test results, the plant will be placed on the Department's Production Facility Listing. The cementitious materials supplier shall utilize a QC Plan accepted by the ~~State Materials Office~~. The Department reserves the right to withdraw QC Plan acceptance and to require cementitious material shipments to be individually tested prior to incorporation into Department work. QC Plans may be suspended when the performance of cementitious material is in question, including problems with concrete quality, inconsistent QC data, or failure of QC or verification test results.

Repulpable bags may be accepted by the Engineer, provided a successful demonstration by the producer has indicated complete degradation of the repulpable bags during the mixing operation and before the mix is discharged.

929-1.2 Approved Laboratory: A laboratory that is currently inspected by the Cement and Concrete Reference Laboratory (CCRL), is actively participating in the CCRL proficiency program and has corrected all deficiencies noted at the time of inspection. The laboratory must authorize the CCRL to send a copy of the final inspection report and proficiency sample results to the ~~State Materials Office~~.

929-2 Fly Ash.

929-2.1 General: Sampling and testing of fly ash shall follow the requirements of ASTM C311. Fly ash shall not include the residue resulting from the burning of municipal ~~garbage waste~~ or any other refuse with coal, or the burning of industrial or municipal ~~garbage waste~~ in incinerators.

929-2.2 Fly Ash (Class F): Fly ash derived from the combustion of ground or powdered coal shall meet the requirements of ASTM C618 Class F fly ash.

929-2.2.1 Petroleum Coke Class F: Fly ash resulting from the combustion of coal and petroleum coke shall meet the physical and chemical requirements of ASTM C618 Class F fly ash. When petroleum coke Class F fly ash is used in concrete, the test results shall verify improved or comparable strength, sulfate resistance, corrosion protective properties and other durability requirements of concrete, as compared to ASTM C618 Class F fly ash concrete. The strength and durability tests of concrete shall be performed in accordance with ASTM C39, ASTM C157, FM 3-C1012, FM 5-516 and AASHTO T358.

929-2.2.2 Bark Ash Class F: Fly ash resulting from the combustion of timber bark ash and coal shall meet the physical and chemical requirements of ASTM C618 Class F fly ash. When bark ash is used in concrete, test results shall verify improved or comparable strength, sulfate resistance, corrosion protective properties, and other durability requirements of concrete, as compared to ASTM C618 Class F fly ash concrete. The strength and durability tests of concrete shall be performed in accordance with ASTM C39, ASTM C157, AASHTO T358, FM 3-C1012, and FM 5-516.

929-2.3 Fly Ash (Class C): Fly ash derived from the combustion of ground or powdered coal shall meet the requirements of ASTM C618 Class C fly ash. When Class C fly ash is used in concrete, the test results shall verify improved or comparable strength, sulfate resistance, corrosion protective properties, and other durability requirements of concrete, as compared to ASTM C618 Class F fly ash concrete. The strength and durability tests of concrete shall be performed in accordance with ASTM C39, ASTM C157, AASHTO T358, FM 3-C1012, and FM 5-516.

929-2.4 Exceptions: Fly ash shall not be used in conjunction with Type IP or Type IS cements.

929-2.5 Acceptance Testing of Fly Ash: Acceptance of fly ash from sources operating under an approved QC Plan shall be based on the monthly certified test report meeting the chemical and physical requirements of ASTM C618. When the loss on ignition exceeds 5%, the Supplementary Optional Physical Requirements shall be mandatory except that the Effectiveness in Controlling Alkali-Silica Reaction will not be required. An approved laboratory shall perform the monthly QC tests and a copy of their certified test reports shall be sent to the [State Materials Office](#) when the material is in use on Department projects. The certification shall indicate that the fly ash meets the requirements of this Specification. Also, the corresponding samples along with certified test reports shall be submitted to the Department, upon request.

929-3 Slag.

929-3.1 General: Slag shall meet the requirements of ASTM C989. Sampling and testing procedures shall follow the requirements of ASTM C989.

929-3.2 Special Requirements: Only ground granulated blast-furnace slag Grade 100 and 120 will be permitted.

929-3.3 Exceptions: Slag shall not be used in conjunction with Type IP or Type IS cements.

929-3.4 Acceptance Testing: Acceptance of slag from sources operating under an approved QC Plan shall be based on the monthly certified QC tests meeting the chemical and physical requirements of ASTM C989. An approved laboratory shall perform the monthly QC tests and a copy of their mill certificates shall be sent to the SMO when the material is in use on Department projects. Reference cement used for determination of slag activity shall meet the requirements of ASTM C989. The certification shall indicate that the slag meets the requirements of this Specification. Also, the corresponding samples along with mill certificates shall be submitted to the Department, upon request.

929-4 Highly Reactive Pozzolans.

929-4.1 Silica Fume:

929-4.1.1 General: Silica Fume shall meet the requirements of ASTM C1240 using the referenced test methods and frequencies.

929-34.1.2 Acceptance Testing of Silica Fume: Acceptance of silica fume from sources operating under an approved QC Plan shall be based on certification that the material meets the requirements of ASTM C1240 and this Specification.

929-4.2 Metakaolin:

929-4.2.1 General: Metakaolin shall meet the requirements of ASTM C618 Class N with the following modifications:

1. The sum of $\text{SiO}_2 + \text{Al}_2\text{O}_3 + \text{Fe}_2\text{O}_3$ shall be at least 85%.
2. The loss on ignition shall be less than 3.0%.
3. The available alkali's, as equivalent Na_2O , shall not exceed 1.0%.
4. The strength activity Index, at 7 days, shall be at least 85%.
5. When metakaolin is used in concrete, the test results shall verify improved or comparable strength, sulfate resistance, corrosion protective properties and other durability performance properties of concrete, as compared to the performance of silica fume concrete. The comparison strength and durability tests shall be performed in accordance with ASTM C39, ASTM C157, FM 3-C1012, FM 5-516, and AASHTO T358, by an independently approved testing laboratory. Sampling and testing of metakaolin shall follow the requirements of ASTM C311.

929-4.2.2 Acceptance Testing of Metakaolin: Acceptance of metakaolin from sources operating under an approved QC Plan shall be based on the monthly certified test report meeting the chemical and physical requirements of ASTM C618 Class N, as modified herein. An approved laboratory shall perform the monthly QC tests and a copy of their certified test reports shall be sent to the ~~State Materials Office~~, when the material is in use on Department projects. Also, the corresponding samples along with certified test reports shall be submitted to the Department, upon request. The certification shall indicate that the metakaolin meets the requirements of this Specification.

~~929-5 Slag:~~

~~929-5.1 General: Slag shall meet the requirements of ASTM C989. Sampling and testing procedures shall follow the requirements of ASTM C989.~~

~~929-5.2 Special Requirements: Only ground granulated blast furnace slag Grade 100 and 120 will be permitted.~~

~~929-5.3 Exceptions: Slag shall not be used in conjunction with Type IP or Type IS cements.~~

~~929-5.4 Acceptance Testing: Acceptance of slag from sources operating under an approved QC Plan shall be based on the monthly certified QC tests meeting the chemical and physical requirements of ASTM C989. An approved laboratory shall perform the monthly QC tests and a copy of their mill certificates shall be sent to the State Materials Office when the material is in use on Department projects. Reference cement used for determination of slag activity shall meet the requirements of ASTM C989. The certification shall indicate that the slag meets the requirements of this Specification. Also, the corresponding samples along with mill certificates shall be submitted to the Department, upon request.~~

~~929-6 Ultra Fine Fly Ash:~~

929-4.3 Ultra Fine Fly Ash:

929-64.3.1 General: Sampling and testing of the ultra fine fly ash shall follow the requirements of ASTM C311. Ultra fine fly ash derived from the combustion of ground or

powdered coal shall meet the requirements of ASTM C618 as a Class F fly ash with the following modifications:

- _____ 1. The pozzolanic activity index, at 7 days, shall be at least 85% of the control and the pozzolanic activity index, at 28 days, shall be at least 95% of the control.
- _____ 2. Particles less than 3.25 microns shall be at least 50% of the particle size distribution, as measured by laser particle size analyzer. Particles less than 8.50 microns shall be at least 90% of the particle size distribution, as measured by laser particle size analyzer.
- _____ 3. The amount of material retained when wet-sieved on a 45- μ m sieve shall be less than 6.0%.
- _____ 4. The moisture content shall be less than 1.0%.
- _____ 5. The loss on ignition shall be less than 2.0%.

_____ **929-64.3.2 Exceptions:** Ultra fine fly ash shall not be used in conjunction with Type IP or Type IS cements.

_____ **929-64.3.3 Acceptance Testing of Ultra Fine Fly Ash:** Acceptance of fly ash from sources operating under an approved QC Plan shall be based on the monthly certified test report meeting the chemical and physical requirements of ASTM C618. When the loss on ignition exceeds 2.0%, the Uniformity Requirements in the Supplementary Optional Physical Requirements shall be mandatory. An approved laboratory shall perform the monthly QC tests and a copy of their certified test reports shall be sent to the ~~State Materials Office~~ when the material is in use on Department projects. The certification shall indicate that the fly ash meets the requirements of this Specification. Also, the corresponding samples along with certified test reports shall be submitted to the Department, upon request.