

EXPECTED IMPLEMENTATION JULY 2020

288 CEMENT TREATED PERMEABLE BASE (REV 10-16-19) (FA 1-7-20) (7-20)

ARTICLE 288-2 is deleted and the following substituted:

288-2 Materials.

Meet the following requirements:

Coarse Aggregate.....	Section 901
Portland Cement.....	Section 921
Water.....	Section 923
Polyvinyl-Chloride Pipe.....	Section 948
Polyethylene Pipe.....	Section 948
Geotextile Fabric.....	Section 985

For Cement Treated Permeable Base, the concrete requirements of Section 346 are modified as follows:

Use Type I or II portland cement (no supplementary cementitious materials permitted).

Composition:

Grade of coarse aggregate (stone).....	# 57 or # 67
Maximum Water/Cement ratio*	0.40
Minimum cement factor**	9 lb/ft ³
Maximum Slump Range	Not Applicable
Fine Aggregate.....	None
Admixtures.....	None

*The Engineer will approve the Water/Cement ratio.

** ± 2 lbs/ft³

Do not use materials which contain hardened lumps, crusts, or frozen matter, or are contaminated with dissimilar material.

D

R

A

F

T