

EXPECTED IMPLEMENTATION JULY 2021

916 BITUMINOUS MATERIALS (REV 10-28-20) (FA 1-15-21) (7-21)

SUBARTICLE 916-2.3 is deleted and the following substituted:

916-2.3 Reporting: Specification compliance testing results shall be reported for the tests in Table 916-1 below, unless noted otherwise. Quality control (QC) testing results shall be reported for original binder DSR ($G/\sin \delta$ and phase angle, as applicable).

Table 916-1		
SUPERPAVE PG ASPHALT BINDER		
Test and Method	Conditions	Specification Minimum/Maximum Value
Superpave PG Asphalt Binder Grade		Report
APL Number		Report
Modifier (name and type)	Polymer, Ground Tire Rubber with Approved Product List (APL) number, Sulfur, PPA, REOB, and any Rejuvenating Agents	Report
Original Binder		
Solubility, AASHTO T44-14 (2018)	in Trichloroethylene	Minimum 99.0% (Not applicable for PG 76-22 (ARB))
Flash Point, AASHTO T 48-18	Cleveland Open Cup	Minimum 450°F
Rotational Viscosity, AASHTO T 316-19	275°F	Maximum 3 Pa·s ^(a)
Dynamic Shear Rheometer ^(b) , AASHTO T 315-19	$G^*/\sin \delta$	Minimum 1.00 kPa
	Phase Angle, δ ^(c) PG 76-22 (PMA) and PG 76-22 (ARB) ^(d)	Maximum 75 degrees
Separation Test, ASTM D7173-20 and Softening Point, AASHTO T 53-09 (2018)	163±5°C	Maximum 15°F (PG 76-22 (ARB) only)
	48 hours	
Rolling Thin Film Oven Test Residue (AASHTO T240-13 (2017))		
Rolling Thin Film Oven, AASHTO T240-13 (2017)	Mass Change %	Maximum 1.00

EXPECTED IMPLEMENTATION JULY 2021

D

R

A

F

T

Multiple Stress Creep Recovery, $J_{nr, 3.2}$ AASHTO T 350-19	Grade Temperature (Unmodified binders only)	“S” = 4.50 kPa ⁻¹ max
Multiple Stress Creep Recovery, $J_{nr, 3.2}$ ^(d, e, f) AASHTO T 350-19	67°C (Modified binders only) 76°C (High Polymer binder only)	“V” = 1.00 kPa ⁻¹ max Maximum $J_{nr, diff} = 75\%$ 0.10 kPa ⁻¹ max
Multiple Stress Creep Recovery, %Recovery ^(d, e) AASHTO T 350-19	67°C (Modified binders only) 76°C (High Polymer binder only)	$\%R_{3.2} \geq \frac{29.371 (J_{nr, 3.2})}{0.2633}$ $\%R_{3.2} \geq 90.0$
Pressure Aging Vessel Residue (AASHTO R 28-12 (2016))		
Dynamic Shear Rheometer, AASHTO T 315-19	$G^* \sin \delta$, 10 rad/sec.	Maximum 5,000 kPa ^(g) Maximum 6,000 kPa ^(h)
Creep Stiffness, AASHTO T 313-19	S (Stiffness), @ 60 sec. m-value, @ 60 sec.	Maximum 300 MPa Minimum 0.300
ΔT_c , ASTM D7643-16	20 hours PAV aging S (Stiffness), @ 60 sec. m-value, @ 60 sec.	$\Delta T_c \geq -5.0^\circ\text{C}$
<p>(a) Binders with values higher than 3 Pa·s should be used with caution and only after consulting with the supplier as to any special handling procedures, including pumping capabilities.</p> <p>(b) Dynamic Shear Rheometer (AASHTO T 315-19) shall be performed on original binders for the purposes of QC testing only. The original binder $G^*/\sin \delta$ shall be performed at grade temperature. Grade temperature for High Polymer binder is 76°C.</p> <p>(c) The original binder phase angle (AASHTO T 315-19) shall be performed at grade temperature.</p> <p>(d) AASHTO T 315-19 and AASHTO T 350-19 will be performed at a 2-mm gap for PG 76-22 (ARB).</p> <p>(e) All binders with a high temperature designation >67 will be tested at 67°C. PG 76-22 (PMA) and PG 76-22 (ARB) shall pass a “V” grade per AASHTO M 332-19.</p> <p>(f) A maximum $J_{nr, diff} = 75\%$ does not apply for any J_{nr} value ≤ 0.50 kPa⁻¹.</p> <p>(g) For PG 67, perform the PAV residue testing at 26.5°C with a maximum of 5,000 kPa.</p> <p>(h) For PG 76 or higher, perform the PAV residue testing at 26.5°C with a maximum of 6,000 kPa.</p>		