

# EXPECTED IMPLEMENTATION JULY 2022

## ROCK BASE

(REV 10-19-21) (FA 2-7-22) (7-22)

SUBARTICLE 200-2.2 is deleted and the following substituted:

**200-2.2 Existing Rock:** Meet the following requirements for use of existing rock on the same project:

1. Notify the Engineer in writing prior to excavating existing rock. Do not mill any existing rock from the roadway.

2. Submit a process control plan, herein referred to as “Plan” consisting of the following:

a. Locations where existing rock will be removed from the roadway.

b. Locations where existing rock will be used for new construction.

c. Method of excavation, transport, and placement to ensure excavated rock will be kept separate from other approved stockpiles. Excavation methods that may result in damage to the rock rendering it unfit to be used as base will not be approved.

d. Proposed measures to prevent contamination and segregation.

e. Proposed locations and methods for constructing stockpiles for sampling and testing.

f. Method for sampling and reporting test results.

3. The Engineer will coordinate the review of the “Plan” with the District Materials Office.

4. Upon the Engineer’s review of the “Plan”, build a preliminary stockpile, not to exceed 1,000 cubic yards.

5. Collect and test a minimum of three samples from the preliminary stockpile. Once the stockpile has been sampled, do not add any additional material to the stockpile. Determine compliance with 200-2.1, with the exception of carbonate contents. Reject any stockpile if the Limerock Bearing Ratio (LBR) is less than 100. The Engineer will sample and test the preliminary stockpile to verify compliance with this Section.

6. If all test results meet the requirements of this Section, the Engineer will notify the Contractor in writing of the approved status of the preliminary stockpile based on the analysis of test data performed by the District Materials Office.

7. If the use of existing rock is approved, continue to produce additional stockpiles not exceeding 1,000 cubic yards. Ensure the rock meets the requirements of this Section by sampling and testing each new stockpile at a minimum frequency of one sample per 400 cubic yards. Once a stockpile has been sampled, do not add additional material to that stockpile. The District Materials Office may also perform sampling and testing. Materials will be accepted if test results meet the requirements of this Section.

8. After 10 consecutive quality control (QC) LBR test results meet the requirements of the Section and no individual LBR test is less than 120, the sampling and testing frequency may be reduced to a minimum frequency of one sample per 800 cubic yards for each stockpile. Notify the Engineer in writing prior to reducing testing

# EXPECTED IMPLEMENTATION JULY 2022

frequency. If any QC LBR test result falls below 120 or a stockpile is rejected, revert to original sampling frequency of one sample per 400 cubic yards.

9. Construct a new preliminary stockpile if there is a change in material, conditions not addressed in the “Plan” are encountered, or if production varies from the approved “Plan”.

## **200-7 Acceptance Program.**

**200-7.1 General Requirements:** Meet the requirements of 120-10, except exclude the requirements of 120-10.1.4.3, 120-10.3.1, 120-10.4.3, and 120-10.4.4. Use 200-7.3.1.1 instead of 120-10.1.4.1, 200-7.2 instead of 120-10.2, and 200-7.4.1 instead of 120-10.4.1.

