

# EXPECTED IMPLEMENTATION JULY 2022

## 350 CEMENT CONCRETE PAVEMENT.

(REV 12-7-21) (FA 12-16-21) (7-22)

ARTICLE 350-2 is deleted and the following substituted:

### 350-2 Materials.

Meet the following requirements except as modified herein:

Concrete .....	Section 346
Grinding Concrete Pavement.....	Section 352
Curing Materials* .....	Section 925
Embedded Items.....	Section 931
Joint Seal.....	Section 932

\*Use products listed on the Department's Approved Product List (APL).

Provide concrete with a minimum 28-day compressive strength of 3,000 psi and maximum water to cementitious materials ratio of 0.50.

For concrete pavement placed using the slip-form method of construction, utilize concrete with a target slump of 1.5 inches plus or minus 1 inch. For concrete pavement placed by hand in constructed forms, utilize concrete with a target slump of 3 inches plus or minus 1.5 inches. Air content testing for concrete pavement mixes is not required.

