## ORIGINATION FORM Proposed Revisions to the Specifications

(Please provide all information - incomplete forms will be returned)

Date:	Office:
Originator:	Specification Section:
Telephone:	Article/Subarticle:
email:	Associated Section(s) Revisions:

Will the proposed revision require changes to:

Publication	Yes	No	Office Staff Contacted
Standard Plans Index			
Traffic Engineering Manual			
FDOT Design Manual			
Construction Project Administration Manual			
Basis of Estimate/Pay Items			
Structures Design Guidelines			
Approved Product List			
Materials Manual			

Will this revision necessitate any of the following:

Design Bulletin	Construction Bulletin	Estimates Bulletin		Materials Bulletin
Are all references to ex	cternal publications current?	Yes	No	

If not, what references need to be updated? (Please include changes in the redline document.)

Why does the existing language need to be changed?

Summary of the changes:

Are these changes applicable to all Department jobs? If not, what are the restrictions?

Yes

No



**MEMORANDUM** 

**DATE:** December 2, 2021

**RON DESANTIS** 

GOVERNOR

**TO:** Specification Review Distribution List

**FROM:** Daniel Strickland, P.E., State Specifications Engineer

## SUBJECT: Proposed Specification: 4620704 Post-Tensioning.

In accordance with Specification Development Procedures, we are sending you a copy of a proposed specification change.

This change was proposed by Ben Goldsberry from the Structures Design Office to allow PT systems to be accepted through the shop drawing submittal process instead of through a preapproved list.

Please share this proposal with others within your responsibility. Review comments are due within four weeks and should be sent to Mail Station 75 or online at <a href="http://fdotewp1.dot.state.fl.us/programmanagement/development/industryreview.aspx">http://fdotewp1.dot.state.fl.us/programmanagement/development/industryreview.aspx</a> . Comments received after <a href="http://gotewp1.dot.state.fl.us/programmanagement/development/industryreview.aspx">http://fdotewp1.dot.state.fl.us/programmanagement/development/industryreview.aspx</a> . Comments received after <a href="http://gotewp1.dot.state.fl.us/programmanagement/development/industryreview.aspx">http://fdotewp1.dot.state.fl.us/programmanagement/development/industryreview.aspx</a> .

DS/ra

Attachment

## POST-TENSIONING. (REV 11-10-21)

SUBARTICLE 462-7.4.2.1.5.3 is deleted and the following substituted:

## 462-7.4.2.1.5.3 Operations:

1. Open all inlets, outlets, drains and ports before beginning the wax injection operation to remove standing water from duct. Capture and measure the water removed from the duct. If the volume of water is significant, as determined by the Engineer, then utilize compressed air, vacuuming, or other means deemed acceptable by the Engineer to dry the duct interior.

etc.

2. Protect concrete surfaces from wax spills, leaks,

3. Inject wax in accordance with approved Wax

Injection Operations Plan.

4. Use pumping methods that ensure complete

filling of ducts and anchorage assembly with wax.

5. Ensure the entire mass of wax is fully liquefied prior to and throughout injection operations. Establish a non-turbulent, laminar system circulation by continuously recirculating the wax between the pump and the storage container prior to injecting the wax into the duct. Pump components must be at wax injection temperature prior to wax injection into duct. Do not allow wax to free fall during recirculation or injection operations. Maintain a positive head of liquid wax above all withdrawal and recirculation ports and do not allow air intrusion into the pumping system. Do not pour liquid wax into an open pump or hopper.

6. Inject PT wax at a continuous and steady rate in accordance with the approved Wax Injection Operations Plan at a flow rate through duct at a velocity between 40 and 70 feet per minute and pressure limited to 75 psi at the duct inlet and 145 psi at the pump.

7. For tendons in which vacuum assisted injection is used, provide a minimum of 90% vacuum in the duct prior to injection. Connect both the anchorage outlet and the cap outlet to the vacuum system. After the vacuum is established, lock off the air supply to the duct and monitor the vacuum for 1 minute. If the loss of vacuum after 1 minute exceeds 10%, repair leaks as directed by the Engineer and retest the duct. If the results are acceptable, reestablish and maintain a minimum 90% vacuum using the outlets at the higher end anchorage shown on Standard Plans, Index 462-001 while injecting wax using the inlet at the lower end anchorage shown on the same Standard. Close all outlets, inlets, and ports other than at injection and vacuum locations during injection procedure. Pump wax into inlet and continuously vacuum air at the outlet until duct is fully injected with wax. After the duct is fully injected with wax and the wax reaches the vacuum end, close the outlet valve, turn off the vacuum pump and continue the injection pump. Bleed all outlets starting at the anchorage cap at the injection end and proceed to bleed every valve thereafter from injection end to vacuum end, ending with the anchorage cap at the vacuum end. When bleeding each valve, collect a minimum of two gallons of continuously flowing wax free from air before closing the valve. Close outlet valve at anchorage when filled with wax. After all outlet valves are closed, Cclose inlet valve with locking pressure between 30 psi and 45 psi. Do not reuse discharged wax.

4620704 All Jobs

8. For tendons in which vacuum assisted injection is

not used, inject wax under pressure at locations shown on Standard Plans, Index 462-001. Allow wax to flow from duct and anchorage discharge points until a steady flow of wax free from air is continuously discharged. Collect a minimum of two gallons of continuously flowing wax free from air at discharge point before closing outlet valve. Do not reuse discharged wax. After all outlets are closed, close the inlet valve at locking pressure between 30 and 45 psi.

9. Record the total volume of wax injected into the

system.

10. Upon completion of wax injection, seal the duct in accordance with the approved PT system drawings. Remove all excess wax from exposed surfaces.