### **ORIGINATION FORM**

# **Proposed Revisions to the Specifications**

(Please provide all information - incomplete forms will be returned)

Date:	Office:				
Originator:	Specification Section:				
Telephone:	Article/Subarticle:				
email:	Associated Section(s) Revisions:				
Will the proposed revision require changes to:					
Publication	Yes	No	Office S	Staff Contacted	
Standard Plans Index					
Traffic Engineering Manual					
FDOT Design Manual					
Construction Project Administration Manual					
Basis of Estimate/Pay Items					
Structures Design Guidelines					
Approved Product List					
Materials Manual					
		1			
Will this revision necessitate any of the following	ng:				
Design Bulletin Construction Bulletin	E:	stimates Bulle	etin	<b>Materials Bulletin</b>	
Are all references to external publications curre	ent?	Yes	No		
If not, what references need to be updated? (Pl	ease inclu	ıde changes iı	n the redline do	ocument.)	
Why does the existing language need to be cha	ngod2				
willy does the existing language need to be tha	iigeu:				
Summary of the changes:					
Are these changes applicable to all Department If not, what are the restrictions?	jobs?	Yes	No		



RON DESANTIS GOVERNOR

# KEVIN J. THIBAULT, P.E. SECRETARY

#### MEMORANDUM

**DATE:** December 9, 2021

**TO:** Specification Review Distribution List

**FROM:** Daniel Strickland, P.E., State Specifications Engineer

**SUBJECT:** Proposed Specification: **5300200 Revetment Systems.** 

In accordance with Specification Development Procedures, we are sending you a copy of a proposed specification change.

The changes are proposed by Melissa Hollis to update formatting to be consistent with APL requirements in the Standard Specification.

Please share this proposal with others within your responsibility. Review comments are due within four weeks and should be sent to Mail Station 75 or online at <a href="http://fdotewp1.dot.state.fl.us/programmanagement/development/industryreview.aspx">http://fdotewp1.dot.state.fl.us/programmanagement/development/industryreview.aspx</a>. Comments received after January 6, 2022, may not be considered. Your input is encouraged.

Comments received after **January 0, 2022**, may not be considered. Tour input is encouraged.

DS/dh

Attachment

# REVETMENT SYSTEMS. (REV 11-23-21)

ARTICLE 530-2 is deleted and the following substituted:

### 530-2 Materials.

without leakage.

## 530-2.1 Riprap:

**530-2.1.1** General Filter Fabric: Meet the following requirements:

Type D-2 Geotextile Fabric\*.....Section 985

\*Use products listed on the Department's APL.

Schedule work so that covering the fabric with the specified material does not exceed the manufacturer's recommendations for exposure to ultraviolet light or five days, whichever is less. If the Engineer determines the exposure time was exceeded, the Contractor shall replace the fabric at no expense to the Department.

Place the filter fabric (fabric) at locations as shown in the Plans, in accordance with the manufacturer's directions. Place the fabric on areas with a uniform slope that are reasonably smooth, free from mounds, windrows, and any debris or projections which might damage the fabric.

Loosely lay the material. Do not stretch the material. Replace or repair any fabric damaged or displaced before or during placement of overlying layers. Repair in accordance with the manufacturer's instructions.

The Contractor may sew the seams to reduce overlaps as specified in 985-3. Follow the manufacturer's instructions for all seams and overlaps.

**530-2.1.2 Prepackaged Sand-Cement Bags:** Provide prepackaged sand-cement bags that meet the following requirements:

- 1. Evenly proportioned sand and cement in the ratio of five cubic feet of sand to 94 pounds of cement. Material proportioned by mass shall use a sand density of 85 pounds per cubic foot.
  - 2. Sealed package of 80 pounds of sand-cement in a bag.
  - 3. Bag made of scrim-reinforced paper capable of holding the sand-cement
  - 4. Sand meets requirements of Section 902-3.3
  - 5. Type I/II cement meets requirements of Section 921.

Prepackaged Sand-Cement Bags shall be one of the products listed on the Department's Approved Product List. Manufacturers seeking evaluation of their product shall submit an application in accordance with Section 6. Include with the submittal a product data sheet, safety data sheet, product label, and a self-certified statement the product meets the requirements of this Section.

#### 530-2.1.3 Rubble:

**530-2.1.3.1 Rubble (Bank and Shore Protection):** Provide sound, hard, durable rubble, free of open or incipient cracks, soft seams, or other structural defects, consisting of broken stone with a bulk specific gravity of at least 2.20. Ensure that stones are rough and angular.

For this application, use broken stone meeting the following gradation and thickness requirements:

Weight Maximum	Weight 50%	Weight Minimum	Minimum Blanket
Pounds	Pounds	Pounds	Thickness in Feet
670	290	60	2.5
Ensure that at least 97% of the material by weight is smaller than Weight Maximum pounds].			
Ensure that at least 50% of the material by weight is greater than Weight 50% pounds].			
Ensure that at least 85% of the material by weight is greater than Weight Minimum pounds.			

**530-2.1.3.2 Rubble (Ditch Lining):** Use sound, hard, durable rubble, free of open or incipient cracks, soft seams, or other structural defects, consisting of broken stone or broken concrete with a bulk specific gravity of at least 1.90. Ensure that stones or broken concrete are rough and angular.

Use broken stone or broken concrete meeting the following gradation and thickness requirements:

Weight Maximum	Weight 50%	Weight Minimum	Minimum Blanket
Pounds	Pounds	Pounds	Thickness in Feet
75	30	4	1.5
Ensure that at least 97% of the material by weight is smaller than Weight Maximum pounds.			
Ensure that at least 50% of the material by weight is greater than Weight 50% pounds].			
Ensure that at least 90% of the material by weight is greater than Weight Minimum pounds].			

### 530-2.1.3.3 Physical Requirements of Broken Stone and Broken

**Concrete:** Use broken stone and broken concrete meeting the following physical requirements:

Absorption (FM 1-T 85)	Maximum 5%
Los Angeles Abrasion (ASTM C535)	Maximum loss 45%*
Soundness (Sodium Sulphate) (AASHTO T 104)	Maximum loss 12%** (after five cycles)
Flat and elongated pieces	Materials with least dimension less than one third of greatest dimension not exceeding 10% by weight.
Dirt and Fines	Materials less than 1/2 inch in maximum dimension accumulated from interledge layers, blasting or handling operations not exceeding 5% by weight.
Drop Test***(EM 1110-2-2302)	No new cracks developed, or no existing crack widened additional 0.1 inch, or final largest dimension greater than or equal to 90% original largest dimension of dropped piece.

<sup>\*</sup> Ensure that granite does not have a loss greater than 55% and that broken concrete does not have a loss greater than 45%.

\*\* The Engineer may accept rubble exceeding the soundness loss limitation if performance history shows that the material will be acceptable for the intended use. The Engineer will waive the soundness specification for rubble riprap (broken stone and broken concrete) when project documents indicate it will be placed in or adjacent to water or soil with a sulfate content less than 150 parts per million and a pH greater than 5.0.

<sup>\*\*\*</sup> The Engineer will waive the Drop Test unless required to ensure structural integrity. Provide all equipment, labor and testing at no expense to the Department. EM refers to the US Army Corps of Engineer's Specification Engineering Method.

**530-2.1.3.4 Source Approval and Project Control:** The Engineer will approve construction aggregate sources in accordance with 6-2.3.

- 1. The Engineer may perform Independent Verification tests on all materials placed on the project.
- 2. The Engineer will check the gradation of the riprap by visual inspection at the project site. Resolve any difference of opinion with the Engineer in accordance with the method provided in FM 5-538. Provide all equipment, labor, and the sorting site at no expense to the Department.
- 3. The Engineer may test components in a blend of rubble processed from different geologic formations, members, groups, units, layers or seams. The Engineer may select components based on like color, surface texture, porosity, or hardness. The Engineer will reject any blend if a component that makes up at least five percent by volume of the blend does not meet these specifications.

**530-2.1.4 Bedding Stone:** Use Bedding Stone of either a durable quality limestone or other quarry run stone, with a bulk specific gravity of not less than 1.90 and that is reasonably free from thin, flat and elongated pieces. Ensure that the bedding stone is also reasonably free from organic matter and soft, friable particles. Meet the following gradation limits:

Standard Sieve Sizes - Inches	Individual Percentage by Weight Passing
12 inches	100
10 inches	70 to 100
6 inches	60 to 80
3 inches	30 to 50
1 inch	0 to 15

The Engineer will conduct source approval and project control of bedding stone as specified in 530-2.1.3.4. In lieu of limestone or other quarry run stone, the Contractor may substitute non-reinforced concrete from existing pavement that is to be removed and which meets the above requirements for commercial bedding stone.

**530-2.2 Articulating Concrete Block (ACB) Revetment Systems:** Obtain all precast block, cabling, anchors, and necessary incidental materials from the same manufacturer. ACB revetment systems must meet the requirements of ASTM D6684, ASTM D7276 and ASTM D7277. Submit to the Engineer certification from the manufacturer that the ACB revetment system meets the requirements of this Section.

ACB system components must meet the following requirements:

Concrete	Section 347, ASTM D6684
Cables and Fittings	ASTM D6684
Type D-2 Geotextile Fabric *.	Section985
Granular Underlay	Section -901
VII	

\*Use products listed on the Department's APL.

Cables must maintain at least 85% of original tensile strength (ASTM D638) after 1,000 hours exposure to a saturated solution of calcium hydroxide (pH greater than or equal to 11) at 73°F, plus or minus three degrees. Cables must not exceed a maximum of 0.5% moisture

absorption at seven days, per ASTM D570. Cable crimps must be aluminum or stainless steel Type 304 or 316.

#### **530-2.3 Gabions:**

**530-2.3.1 General:** Provide gabions meeting the requirements of ASTM A974 and ASTM A975 as modified herein.

Allowable Gabion Wire and Connector Material	Substructure Environmental Classification
Polymeric	Any
Metallic	Slightly Aggressive
Metallic – Galvanized and PVC coated	Slightly Aggressive
Metanic – Garvanized and PVC coated	Moderately Aggressive
	Slightly Aggressive
Metallic – Type 304 Stainless Steel, Size W1.4	Moderately Aggressive
(MW10) or larger	Extremely Aggressive (< 2,000 ppm
	Chlorides)
Metallic – Type 316 Stainless Steel, Size W1.4	Any
(MW10) or larger	Any

**530-2.3.2 Metallic Gabions:** The components of metallic gabions must meet the following requirements:

Wire Mesh and Fabric*	ASTM A974 and A975
Spiral Binders, Lacing Wire	, Stiffeners, and Ring Wire
Fasteners	ASTM A974 and A975
Stainless Steel Wire, Wire F	abric, and_
Lacing Wire	
	ASTM A1022

\_\*Wire mesh must be Style 1 or Style 3. Wire fabric must be Style 1 or

Style 5.

**530-2.3.3 Polymeric Gabions:** Polymeric gabions must be constructed in general accordance with ASTM A974 using a single layer of structural geogrid instead of welded wire, and polymeric braid instead of ring wire fasteners. The structural geogrid must be Type\_R-1, 2, 3, 4, or 5 meeting the requirements of Section 985 and the following:

Tensile Strength @2% strain MD*	575_lb/ft
Tensile Strength @ 2% strain XD**	575_lb/ft
Junction Strength (% of Tensile Strength)	90%
Min UV Stability	85%
Min. Carbon Black Content (by Weight)	
da m	

<sup>\*</sup>MD = machine direction

Polymeric braid for seeming polymeric gabions or connecting metallic gabions must have a minimum tensile strength of 400 pounds for a 36 inch long specimen and contain at least 2% carbon black by weight.

**530-2.3.4 Gabion Rock:** Use rock meeting the requirements of ASTM D6711 to fill gabions. The rock must be reasonably free from thin, flat or elongated pieces. Rock size must be at least 1.25 times greater than the aperture size of the wire mesh or fabric. Each range of

<sup>\*\*</sup>XD = cross direction

sizes may allow for a variation of 5% oversize rock by weight, 5% undersize rock by weight, or both.

Physical Property Requirements	Acceptable Range
Los Angeles Abrasion and ASTM C535	Maximum loss 40%
Bulk Specific Gravity	Minimum 2.20
Absorption, ASTM C127 and ASTM C128	Maximum 3%

**530-2.3.5 Miscellaneous Components:** Miscellaneous components for gabion installations must meet the following requirements:

Τ	Type D-2 Geotextile Fabric*	Section 985
(	Granular Underlay	Section 901
A	AnchorsSection 451 or manuf	acturer's recommendations
*	Use products listed on the Depa	rtment's APL.

SUBARTICLE 530-3.1 is deleted and the following substituted:

#### 530-3 Construction and Installation.

**530-3.1 Geotextile Fabric:** Place geotextile fabric under all revetment in accordance with Section 514.

Overlap adjacent strips of fabric a minimum of 24 inches, and anchor them with securing pins (as recommended by the manufacturer) inserted through both strips of fabric along a line through the midpoint of the overlap and to the extent necessary to prevent displacement of the fabric.

Place the fabric so that the upstream (upper) strip of fabric overlaps the downstream (lower) strip.

Stagger vertical laps a minimum of 5 feet. Use full rolls of fabric whenever possible in order to reduce the number of vertical laps.

Do not drop bedding stone or riprap from heights greater than 3 feet onto the fabric.

SUBARTICLE 530-5.4 is deleted and the following substituted:

**530-5.4 Geotextile Fabric:** Include the cost of materials and installation of the geotextile fabric, <u>including any repairs or replacement</u>, in the Contract unit price for riprap or ACB revetment system.