

EXPECTED IMPLEMENTATION JULY 2023

916 BITUMINOUS MATERIALS.

(REV 6-23-22) (FA 9-7-22) (FY 2023-24)

ARTICLE 916-2 is deleted and the following substituted:

916-2 Superpave PG Asphalt Binder.

916-2.1 Requirements: Superpave Performance Graded (PG) asphalt binders, identified as PG 52-28, PG 58-22, PG 67-22, polymer modified asphalt (PMA) binders, PG 76-22 (PMA) and High Polymer, and asphalt rubber binders (ARB), PG 76-22 (ARB), shall meet the requirements of 916-2 and AASHTO 332. When the Contract Documents specify either a PG 76-22 (PMA), PG 76-22 (ARB), or PG 76-22 binder, either binder can be used interchangeably at no additional cost to the Department. All PG asphalt binders shall meet the following additional requirements:

1. The intermediate test temperature at 10 rad/sec. for the Dynamic Shear Rheometer (DSR) test (AASHTO T 315) shall be 26.5°C for PG grades PG 67 and higher.
2. An additional high temperature grade of PG 67 is added for which the high test temperature at 10 rad/sec for the DSR test (AASHTO T 315) shall be 67°C.
3. All PG asphalt binders having a high temperature designation of PG 67 or lower shall be prepared without modification.
4. All PMA binders having a high temperature designation higher than PG 67 shall only be produced with a styrene-butadiene-styrene (SBS) or styrene-butadiene (SB) elastomeric polymer modifier and the resultant binder shall meet all requirements of this Section.
5. Polyphosphoric acid may be used as a modifier not exceeding 0.75% by weight of asphalt binder for PG 76-22 (PMA) and PG 76-22 (ARB) binders. Polyphosphoric acid may not be used in High Polymer binder.
6. PG 76-22 (ARB) shall meet the additional requirements of 916-2.1.1.
7. All PG asphalt binders having a high temperature designation of PG 67 or lower shall not have a high temperature true grade more than 5.9°C higher than the specified PG grade, (for example, if a PG 58-22 is specified, do not supply a PG 64-22 or higher).
8. The use of waste oil is prohibited in the modification of any PG binder grade. Waste oil shall be defined as recycled oil products that have not been processed through a vacuum tower and have an initial boiling point of 385°C (725°F) or lower when tested in accordance with ASTM D6352.
9. Re-refined engine oil bottoms (REOB)/vacuum tower asphalt extenders (VTAE) may be used as a modifier not exceeding 8.0% by weight of asphalt binder. REOB/VTAE are materials as defined in Asphalt Institute document IS-235.

For all PG binder used in all hot mix asphalt, silicone may be added to the PG binder at the rate of 25 cubic centimeters of silicone mixed to each 5,000 gallons of PG binder. If a disbursing fluid is used in conjunction with the silicone, the resultant mixture containing the full 25 cubic centimeters of silicone shall be added in accordance with the manufacturer's recommendation. The blending of the silicone with the PG binder shall be done by the supplier prior to the shipment. When the asphalt binder will be used with a foaming warm mix technology, refer to the technology supplier's guidance on the addition of silicone.

EXPECTED IMPLEMENTATION JULY 2023

Where an anti-strip additive is required, the anti-strip additive shall meet the requirements of 916-4. The anti-strip additive shall be introduced into the PG binder by the supplier during loading.

916-2.1.1 Additional Requirements for PG 76-22 (ARB): The following additional requirements apply only to PG 76-22 (ARB):

1. The asphalt binder shall contain a minimum of 7.0% ground tire rubber (GTR) by weight of asphalt binder.
2. The GTR shall meet the requirements of Section 919.
3. Polymer modification is optional for PG 76-22 (ARB).

916-2.1.2 High Polymer Binder Blending: Existing high polymer binder may be blended in an asphalt producer's storage tank to make a PG 76-22 binder provided the following requirements are met:

1. Notify the State Materials Office (SMO) and the local District Materials Office prior to blending.
2. Follow the blending instructions of the high polymer binder supplier.
3. Submit a sample of the blended binder to a SMO approved laboratory for testing. Provide test results to the SMO.
4. Use the newly blended binder only after approval from the SMO.

916-2.2 Compliance with Materials Manual: Producers of Superpave PG binders shall meet the requirements of Section 3.5, Volume II of the Department's Material Manual, which may be viewed at the following URL:

<https://www.fdot.gov/programmanagement/Implemented/URLinSpecs/Section35V2.shtm>

916-2.3 Reporting: Specification compliance testing results shall be reported for the tests in Table 916-1 below, unless noted otherwise. Quality control (QC) testing results shall be reported for original binder DSR ($G/\sin \delta$ and phase angle, as applicable).

EXPECTED IMPLEMENTATION JULY 2023

U
R
A
T

| Table 916-1 SUPERPAVE PG ASPHALT BINDER | | |
|--|---|--|
| Test and Method | Conditions | Specification Minimum/Maximum Value |
| Superpave PG Asphalt Binder Grade | | Report |
| APL Number | | Report |
| Modifier (name and type) | Polymer, Ground Tire Rubber with Approved Product List (APL) number, Sulfur, PPA, REOB, and any Rejuvenating Agents | Report |
| Original Binder | | |
| Solubility, AASHTO T 44 | in Trichloroethylene | Minimum 99.0% (Not applicable for PG 76-22 (ARB)) |
| Flash Point, AASHTO T 48 | Cleveland Open Cup | Minimum 450°F |
| Rotational Viscosity, AASHTO T 316 | 275°F | Maximum 3 Pa·s ^(a) |
| Dynamic Shear Rheometer ^(b) , AASHTO T 315 | $G^*/\sin \delta$ | Minimum 1.00 kPa |
| | Phase Angle, $\delta^{(c)}$ PG 76-22 (PMA) and PG 76-22 (ARB) ^(d) | Maximum 75 degrees |
| Separation Test, ASTM D7173 and Softening Point, AASHTO T 53 | 163±5°C | Maximum 15°F (PG 76-22 (ARB) only) |
| | 48 hours | |
| Rolling Thin Film Oven Test Residue (AASHTO T 240) | | |
| Rolling Thin Film Oven, AASHTO T 240 | Mass Change % | Maximum 1.00 |
| Multiple Stress Creep Recovery, $J_{nr, 3.2}$ AASHTO T 350 | Grade Temperature (Unmodified binders only) | “S” = 4.50 kPa ⁻¹ max |
| Multiple Stress Creep Recovery, $J_{nr, 3.2}^{(d, e, f)}$ AASHTO T 350 | 67°C (Modified binders only) | “V” = 1.00 kPa ⁻¹ max Maximum $J_{nr, diff}$ = 75% 0.10 kPa ⁻¹ max |
| | 76°C (High Polymer binder only) | |

EXPECTED IMPLEMENTATION JULY 2023

0
R
A
T

| Table 916-1 SUPERPAVE PG ASPHALT BINDER | | |
|--|--|--|
| Multiple Stress Creep Recovery, %Recovery ^(d, e) AASHTO T 350 | 67°C (Modified binders only) | $\%R_{3.2} \geq 29.371 (J_{nr, 3.2})^{0.2633}$ |
| | 76°C (High Polymer binder only) | $\%R_{3.2} \geq 90.0$ |
| Pressure Aging Vessel Residue (AASHTO R 28) | | |
| Dynamic Shear Rheometer, AASHTO T 315 | $G^* \sin \delta$, 10 rad/sec. | Maximum 6,000 kPa ^(g,h) |
| Creep Stiffness, AASHTO T 313 | S (Stiffness), @ 60 sec. m-value, @ 60 sec. | Maximum 300 MPa Minimum 0.300 |
| ΔT_c , ASTM D7643 | 20 hours PAV aging S (Stiffness), @ 60 sec. m-value, @ 60 sec. | $\Delta T_c \geq -5.0^\circ\text{C}$ |
| <p>(a) Binders with values higher than 3 Pa·s should be used with caution and only after consulting with the supplier as to any special handling procedures, including pumping capabilities.</p> <p>(b) Dynamic Shear Rheometer (AASHTO T 315) shall be performed on original binders for the purposes of QC testing only. The original binder $G^*/\sin \delta$ shall be performed at grade temperature. Grade temperature for High Polymer binder is 76°C.</p> <p>(c) The original binder phase angle (AASHTO T 315) shall be performed at grade temperature.</p> <p>(d) AASHTO T 315 and AASHTO T 350 will be performed at a 2-mm gap for PG 76-22 (ARB).</p> <p>(e) All binders with a high temperature designation >67 will be tested at 67°C. PG 76-22 (PMA) and PG 76-22 (ARB) shall pass a “V” grade per AASHTO M 332.</p> <p>(f) A maximum Jnr diff = 75% does not apply for any Jnr value ≤ 0.50 kPa-1.</p> <p>(g) For $5000 \text{ kPa} \leq G^* \sin \delta \leq 6,000 \text{ kPa}$, the phase angle, δ, shall be a minimum of 42°.</p> <p>(h) For PG 67 or higher grades, perform the PAV residue testing at 26.5°C.</p> | | |

SUBARTICLE 916-3.2 is deleted and the following substituted:

916-3.2 Requirements: Use a prime coat meeting the requirements of AASHTO M 140 for anionic emulsions, AASHTO M 208 or AASHTO M 316 for cationic emulsions, or as specified in the Producer’s QC Plan. For anionic emulsions, the cement mixing test will be waived. For tack products, the minimum testing requirements shall include percent residue, naphtha content (as needed), one-day storage stability, sieve test, Saybolt Furol viscosity, original DSR, re-emulsification (FM 5-624), and solubility (on an annual basis). Residue testing shall be performed on residue obtained from distillation, AASHTO T 59 or low-temperature evaporation (AASHTO R 78) .

At the direction of the Engineer, sample tack from the distributor used on the project at a minimum frequency of once per project per product. The sample shall be tested by the Department for the following specified material properties: percent residue, contaminants, and the residue property $G^*/\sin \delta$. Should any of the test results fail the specification requirements, the tack material will be considered defective and shall not to be used on Department projects unless waived by the Engineer. Should a tack sample fail specifications, the Engineer may require three 6-inch diameter roadway cores be obtained

EXPECTED IMPLEMENTATION JULY 2023

U
R
A
T
E

from the day of production from which the tack sample was obtained. The roadway cores shall be tested for bond strength in accordance with FM 5-599. Individual bond strength results less than 80 psi will require removal and replacement. Failing bond strength results may result in bond strength testing for additional areas represented by the failing tack material.