

EXPECTED IMPLEMENTATION JULY 2024 (FY 2024-25)

560 COATING NEW STRUCTURAL STEEL. (REV 10-16-23) (FA 9-19-23) (FY 2024-25)

SUBARTICLE 560-2.1 is deleted and the following substituted:

560-2 Materials.

560-2.1 Coating System: Use only coating products and systems meeting the requirements of Section 975 and listed on the Department's Approved Product List (APL). All components of coating systems must be from the same manufacturer.

Use Type M coal tar or modified glass flake epoxy coatings meeting the requirements of Section 926. Apply these products over a primer listed on the Department's APL for coating of permanent bulkhead sheet piles and H piles.

SUBARTICLE 560-11.2 is deleted and the following substituted:

560-11.2 Application of Coating: Unless otherwise shown in the Contract Documents, apply the inorganic zinc primer to all surfaces of H and sheet piles and the exterior surface of pipe piles in accordance with the limitations of 560-8. Unless otherwise shown in the Contract Documents, apply coal tar or modified glass flake epoxy coatings to the exposed side of sheet piles from the top of the piles to a depth of five feet below the lower of the design ground surface or the design scour depth in accordance with the limitations of 560-8. Apply the inorganic zinc primer in accordance with this Section. Apply the coal tar or modified glass flake epoxy in accordance with the following specific requirements:

1. Apply the coal tar or modified glass flake epoxy system in strict accordance with the coating manufacturer's published specifications. Coal tar epoxies must attain a total dry film thickness (zinc primer and coal tar epoxy) at a minimum 18 mils (on each side). Modified glass flake epoxies must attain a total dry film thickness (zinc primer and modified glass flake epoxy) at a minimum 10 mils (on each side).
2. Ensure that no area measurements of the coating is less than 80% of the specified minimum film thicknesses, as determined by AMPP Paint Application Standard No. 2 (PA-2). The total minimum film thickness for any combination of coats will be the sum total of the averages of the specified thickness range of the individual coats.
3. After applying the coating on the steel piles, the Engineer will thoroughly inspect the surfaces and make film thickness measurements at the approximate rate of one for each 25 square feet of area unless deficient thickness is found. In this case, the rate of additional measurements will be increased as required to determine the extent of the deficient area.