

RON DESANTIS GOVERNOR 605 Suwannee Street Tallahassee, FL 32399-0450 JARED W. PERDUE, P.E. SECRETARY

November 6, 2023

Khoa Nguyen Director, Office of Technical Services Federal Highway Administration 3500 Financial Plaza, Suite 400 Tallahassee, Florida 32312

Re: State Specifications Office Section: 965 Proposed Specification: 9650100 General Provisions For Aluminum Items (Including Welding).

Dear Mr. Nguyen:

We are submitting, for your approval, two copies of the above referenced Special Provision.

The changes are proposed by Timothy McCullough to remove the requirement to have oversight by the FDOT audit program.

Please review and transmit your comments, if any, within two weeks (10 business days). Comments should be sent via email <u>daniel.strickland@dot.state.fl.us</u>.

If you have any questions relating to this specification change, please call me at (850) 414-4130.

Sincerely,

Signature on file

Daniel Strickland, P.E. State Specifications Engineer

DS/jb

Attachment

cc: Florida Transportation Builders' Assoc. State Construction Engineer

# GENERAL PROVISIONS FOR ALUMINUM ITEMS (INCLUDING WELDING) (REV 4-28-23)

SECTION 965 is deleted and the following substituted:

#### 965-1 General.

This Section covers the material and fabrication requirements for aluminum components. All <u>Provide</u> aluminum light poles <u>and Gantry</u> J-arms <u>, and railings</u> from <u>pP</u>roducers <u>who are</u> <u>approved in one of the following fabrication categories:</u>

1. American Institute of Steel Construction, Highway Component Manufacturer

2. American Welding Society, Certified Welding Fabricator

<u>3. Canadian Welding Bureau, Fusion Welding of Aluminum (W47.2) currently on</u> the Department's Production Facility Listing. Producers seeking inclusion on the Department's Production Facility Listing must meet the requirements of Section 105.

#### 965-2 Fabrication.

Provide fabricated components in accordance with AASHTO LRFD Specifications for Structural Supports for Highway Signs, Luminaires and Traffic Signals, the Design Plans, and this section. Verify the strength of each Lot by tensile test. Alternate testing will not be accepted. Protect against damage and marring during transit and delivery. Provide an anodic coating (minimum 0.0002 inch) and chromate seal all hardware.

All welds must be visually inspected for final approval by an actively certified welding inspector, qualified through the An American Welding Society certified welding inspector must visually inspect all welds for final approval. A certifying statement from the welding inspector must be provided with the component. The document must identify the project information, date of inspection, welding inspector name, and inspector certification number.

Table 965-1				
Material Requirements for Aluminum Components				
Product	Test Method	Alloy/Temper	Reported Properties	
Pole, Arm, Extrusions	ASTM B221	6061-T6		
Fole, Allii, Extrusions	ASTM D221	6063-T6		
Pedestal, Posts	ASTM B429	6061-T6		
Dava Diotog Stiffenorg	ASTM B221	6063-T6		
Bars, Plates, Stiffeners, Backing Ring, Shims,	ASTM B221	6061-T6		
0 0	ASTM B209	6061-T6		
Shapes	ASTM B308		Allow Tommon	
	ASTM B221	6351-T5	Alloy, Temper, Thickness, Tensile Strength	
	ASTM D221		Thickness, Tensne Strength	
Railing	ASTM B241	6061-T6		
	ASTM B210	0001-10		
	ASTM B429			
J-Arm Tube	ASTM B429	6061-T6		
	ASTM B221			
J-Arm Connection Plate	ASTM B209	6061-T6		

Table 965-1				
Material Requirements for Aluminum Components				
Product	Test Method	Alloy/Temper	Reported Properties	
		6061-T6		
Sheet	ASTM B209	5154-H38		
		5052-H38		
Stress stress 1 Slass as	ASTM B308	(0(1 T(		
Structural Shapes	ASTM B221	6061-T6		
Single Column Ground	ASTM B26	A356-T6		
Sign Sand Castings	ASTM B108	A356-T61		
Washers	ASTM B221	7075-T6		
washers	ASTM D221	2024-T4		
Button Head or Flat	ASTM F468	2024-T4	S2 Lat Tasting Allow Tompor	
Head Bolts	АЗ ПИГ 7408	6061-T6	S2 Lot Testing, Alloy, Temper	
		6061-T6		
Hex Nuts	ASTM F467	6262-T9	S2 Lot Testing, Alloy, Temper	
		2024-T4		

**965-2.1 Light Poles:** Provide aluminum lighting poles in accordance with this section and Table 965-1. Weld arms and poles in the T4 condition, using the filler metal ER4043, ER4047, ER5183, ER5356, or ER5556 in accordance with AWS D1.2 Aluminum Structural welding Code. Weld to castings in accordance with 965-2.3. Heat treat the arm and pole, until aged to the T6 condition. Transverse welds are only allowed at the base. Equip poles with a vibration damper, when specified in the contract documents.

Provide exterior surface with a clean, uniform silvery appearance, free of dark streaks and discoloration. Finish the pole and arm with a satin rubbed finish.

**965-2.2 Overhead Sign Components:** Provide aluminum toll gantry J-arms in accordance with this section and Table 965-1. Weld tube to plate connections in the T4 or T6 condition, using the filler metal ER4043, ER4047, ER5183, ER5356, or ER5556 in accordance with AWS D1.2 Aluminum Structural welding Code. Heat treat tube and plate in the T4 condition until aged to the T6 condition.

Provide exterior surface with a clean, uniform silvery appearance, free of dark streaks and discoloration.

**965-2.3 Castings:** Provide aluminum castings in accordance with this section and Table 965-1. Weld aluminum castings to itself or aluminum tube to castings using the filler metal ER4043, in accordance with AWS D1.2 Aluminum Structural welding Code. Heat treat the castings, until aged to the T6 condition.

**965-2.4 Railing:** Provide aluminum railing in accordance with this section and Table 965-1. Weld aluminum railing using the filler metal ER4043, ER4047, ER5183, ER5356, or ER5556 in accordance with AWS D1.2 Aluminum Structural welding Code.

**965-2.5 Static Sign Assemblies:** Provide aluminum sheet, plate, and structural shapes in accordance with this section and Table 965-1. Weld structural profiles to itself or aluminum components using ER4043, ER4047, ER5183, ER5356 or ER5556 in accordance with AWS D1.2 Aluminum Structural Welding Code. Heat treat the structural profiles, until aged to the T6 condition.

### 965-2.6 Transformer Bases (Excluding Lighting):

**965-2.6.1 Product Acceptance:** Manufacturers seeking evaluation of products for inclusion on the APL shall submit an application in accordance with Section 6 and include the following documentation, showing that the product meets the applicable requirements.

Table 965-2		
Submittal Co	ompliance Requirements	
Documentation	Requirements	
Certified Test Report	Shows that product meets Moment Capacity	
Installation Instructions	Include installation instructions	
Product Identification Photo Display's the manufacturer's name or logo and		
	model number.	
Product Photo	Displays the significant features of the product as	
required in this section.		
Technical Data Sheet or Product	Uniquely identifies the product and includes	
Drawing	product details, notes, material specifications,	
	dimensions, and sizes meeting the specification	

965-2.6.2 Physical Requirements: Meet the requirements of Table 965-3	965-2.6.2 Physical	<b>Requirements:</b>	Meet the rec	quirements of	of Table 965-3.
---	--------------------	----------------------	--------------	---------------	-----------------

Table 965-3				
Physical Requirements for Transformer Base				
Feature	Requirement	Documentation		
Height	Base is 12 to 18 inches in height	Technical Data Sheet or Product Drawing		
Base Material	ASTM B26, 356 T6 or 319	Technical Data Sheet or Product Drawing		
Threaded Hub	Hub located at the top for mounting a nominal 4-inch Schedule 40 (4-1/2-inch outside diameter) aluminum pole. The threaded hub must be tapped to allow full pole engagement.	Technical Data Sheet or Product Drawing		
Fastening	Provides for fastening to a foundation with four 3/4-inch anchor bolts located 90 degrees apart. The base design must allow for bolts that are placed off-center.	Technical Data Sheet or Product Drawing		
Door Size	Provides a door opening of not less than 8 inches by 8 inches.	Technical Data Sheet or Product Drawing		
Door Material	The door must be constructed of fiberglass or other non-combustible, non-aluminum material.	Technical Data Sheet or Product Drawing		

Table 965-3			
	Physical Requirements for Transfor	mer Base	
Door	Attach the door to the base with cleats	Technical Data Sheet or Product	
Attachment	and one stainless steel socket button head	Drawing	
	screw or by other means suitable for		
	NEMA 3 electrical enclosures.		
Moment	Supports an ultimate moment capacity of	Certified Test Report	
Capacity	10,000 foot-pounds, without breaking,		
	cracking or rupturing in any manner.		
Breakaway	Meets the requirements in the AASHTO	FHWA Eligibility Letter.	
	LRFD Specifications for Structural		
	Supports for Highway Signs, Luminaires,		
	and Traffic Signals.		

#### 965-3 Paint for Poles, Pedestals, and Posts.

Paint systems used on aluminum poles, pedestals, and posts shall meet the color requirements as specified in the Contract Documents. All paint systems shall possess physical properties and handling characteristics that are compatible with the application requirements of Section 646. Materials shall be specifically intended for use over aluminum. Paint systems shall exhibit no loss of adhesion or total color difference ( $\Delta E^*_{ab}$ ) greater than 8.0 units for five years after final acceptance as specified in 5-11. An aluminum pole, pedestal, post, or sign panel that exhibits a cumulative surface area of delamination in excess of 50 square inches will constitute an adhesion failure. Delamination shall be defined as any area of exposed metal surface subsequent to hand tool cleaning. A  $\Delta E^*_{ab}$  value exceeding 8.0 units per the International Commission on Illumination L\*a\*b\* 1976 (CIELAB) space and color difference formula, measured in accordance with ASTM D2244, will constitute a color retention failure.

The Department will measure and enter in the Department's database the CIELAB color chromaticity coordinates for the color of the top coat of sample coupons provided as required by 646-2.7 using a BYK-Gardner Handicolor colorimeter using D65 illuminant and 2-degree geometry settings. The Department-measured CIELAB chromaticity coordinates shall define the initial color and will be used for resolution of color retention failures and the resolution of color retention disputes.

#### 965-4 Certification.

Produce a certificate of compliance for non-APL products, upon request of the Engineer. Certificates of compliance shall identify the reportable properties of Table 965-1.

# GENERAL PROVISIONS FOR ALUMINUM ITEMS (INCLUDING WELDING) (REV 4-28-23)

SECTION 965 is deleted and the following substituted:

#### 965-1 General.

This Section covers the material and fabrication requirements for aluminum components. Provide aluminum light poles and Gantry J-arms from Producers who are approved in one of the following fabrication categories:

- 1. American Institute of Steel Construction, Highway Component Manufacturer
- 2. American Welding Society, Certified Welding Fabricator
- 3. Canadian Welding Bureau, Fusion Welding of Aluminum (W47.2).

#### 965-2 Fabrication.

Provide fabricated components in accordance with AASHTO LRFD Specifications for Structural Supports for Highway Signs, Luminaires and Traffic Signals, the Design Plans, and this section. Verify the strength of each Lot by tensile test. Alternate testing will not be accepted. Protect against damage and marring during transit and delivery. Provide an anodic coating (minimum 0.0002 inch) and chromate seal all hardware.

An American Welding Society certified welding inspector must visually inspect all welds for final approval. A certifying statement from the welding inspector must be provided with the component. The document must identify the project information, date of inspection, welding inspector name, and inspector certification number.

Table 965-1				
Material Requirements for Aluminum Components				
Product	Test Method	Alloy/Temper	Reported Properties	
Pole, Arm, Extrusions	ASTM B221	6061-T6		
Pole, Allii, Extrusions	ASTM D221	6063-T6		
Pedestal, Posts	ASTM B429	6061-T6		
Dana Diatas Stiffenana	ASTM B221	6063-T6		
Bars, Plates, Stiffeners,	ASTM D221	6061-T6		
Backing Ring, Shims,	ASTM B209	(0(1 T)		
Shapes	ASTM B308	6061-T6		
	ASTM B221	6351-T5		
	ASTM B221	6061-T6	Alloy, Temper,	
Railing	ASTM B241		Thickness, Tensile Strength	
	ASTM B210			
	ASTM B429			
J-Arm Tube	ASTM B429	6061-T6		
J-AIIII Tube	ASTM B221	0001-10		
J-Arm Connection Plate	ASTM B209	6061-T6		
		6061-T6		
Sheet	ASTM B209	Sheet ASTM B209	5154-H38	
		5052-H38		
Structural Shapes	ASTM B308	6061-T6		

Table 965-1				
Material Requirements for Aluminum Components				
Product	Test Method	Alloy/Temper	<b>Reported Properties</b>	
	ASTM B221			
Single Column Ground	ASTM B26	A356-T6		
Sign Sand Castings	ASTM B108	A356-T61		
Washers	ASTM B221	7075-T6 2024-T4		
Button Head or Flat Head Bolts	ASTM F468	2024-T4 6061-T6	S2 Lot Testing, Alloy, Temper	
Hex Nuts	ASTM F467	6061-T6 6262-T9 2024-T4	S2 Lot Testing, Alloy, Temper	

**965-2.1 Light Poles:** Provide aluminum lighting poles in accordance with this section and Table 965-1. Weld arms and poles in the T4 condition, using the filler metal ER4043, ER4047, ER5183, ER5356, or ER5556 in accordance with AWS D1.2 Aluminum Structural welding Code. Weld to castings in accordance with 965-2.3. Heat treat the arm and pole, until aged to the T6 condition. Transverse welds are only allowed at the base. Equip poles with a vibration damper, when specified in the contract documents.

Provide exterior surface with a clean, uniform silvery appearance, free of dark streaks and discoloration. Finish the pole and arm with a satin rubbed finish.

**965-2.2 Overhead Sign Components:** Provide aluminum toll gantry J-arms in accordance with this section and Table 965-1. Weld tube to plate connections in the T4 or T6 condition, using the filler metal ER4043, ER4047, ER5183, ER5356, or ER5556 in accordance with AWS D1.2 Aluminum Structural welding Code. Heat treat tube and plate in the T4 condition until aged to the T6 condition.

Provide exterior surface with a clean, uniform silvery appearance, free of dark streaks and discoloration.

**965-2.3 Castings:** Provide aluminum castings in accordance with this section and Table 965-1. Weld aluminum castings to itself or aluminum tube to castings using the filler metal ER4043, in accordance with AWS D1.2 Aluminum Structural welding Code. Heat treat the castings, until aged to the T6 condition.

**965-2.4 Railing:** Provide aluminum railing in accordance with this section and Table 965-1. Weld aluminum railing using the filler metal ER4043, ER4047, ER5183, ER5356, or ER5556 in accordance with AWS D1.2 Aluminum Structural welding Code.

**965-2.5 Static Sign Assemblies:** Provide aluminum sheet, plate, and structural shapes in accordance with this section and Table 965-1. Weld structural profiles to itself or aluminum components using ER4043, ER4047, ER5183, ER5356 or ER5556 in accordance with AWS D1.2 Aluminum Structural Welding Code. Heat treat the structural profiles, until aged to the T6 condition.

#### 965-2.6 Transformer Bases (Excluding Lighting):

**965-2.6.1 Product Acceptance:** Manufacturers seeking evaluation of products for inclusion on the APL shall submit an application in accordance with Section 6 and include the following documentation, showing that the product meets the applicable requirements.

Table 965-2		
Submittal Co	ompliance Requirements	
Documentation	Requirements	
Certified Test Report	Shows that product meets Moment Capacity	
Installation Instructions	Include installation instructions	
Product Identification Photo Display's the manufacturer's name or logo and		
model number.		
Product Photo	Displays the significant features of the product as	
required in this section.		
Technical Data Sheet or Product	Uniquely identifies the product and includes	
Drawing	product details, notes, material specifications,	
	dimensions, and sizes meeting the specification	

### 965-2.6.2 Physical Requirements: Meet the requirements of Table 965-3.

Table 965-3					
	Physical Requirements for Transformer Base				
Feature	Requirement	Documentation			
Height	Base is 12 to 18 inches in height	Technical Data Sheet or Product			
		Drawing			
Base Material	ASTM B26, 356 T6 or 319	Technical Data Sheet or Product			
		Drawing			
Threaded Hub	Hub located at the top for mounting a	Technical Data Sheet or Product			
	nominal 4-inch Schedule 40 (4-1/2-inch	Drawing			
	outside diameter) aluminum pole. The				
	threaded hub must be tapped to allow full				
	pole engagement.				
Fastening	Provides for fastening to a foundation	Technical Data Sheet or Product			
	with four 3/4-inch anchor bolts located	Drawing			
	90 degrees apart. The base design must				
	allow for bolts that are placed off-center.				
Door Size	Provides a door opening of not less than	Technical Data Sheet or Product			
	8 inches by 8 inches.	Drawing			
Door Material	The door must be constructed of	Technical Data Sheet or Product			
	fiberglass or other non-combustible, non-	Drawing			
	aluminum material.				

Table 965-3			
	Physical Requirements for Transfor	mer Base	
Door	Attach the door to the base with cleats	Technical Data Sheet or Product	
Attachment	and one stainless steel socket button head	Drawing	
	screw or by other means suitable for		
	NEMA 3 electrical enclosures.		
Moment	Supports an ultimate moment capacity of	Certified Test Report	
Capacity	10,000 foot-pounds, without breaking,		
	cracking or rupturing in any manner.		
Breakaway	Meets the requirements in the AASHTO	FHWA Eligibility Letter.	
	LRFD Specifications for Structural		
	Supports for Highway Signs, Luminaires,		
	and Traffic Signals.		

#### 965-3 Paint for Poles, Pedestals, and Posts.

Paint systems used on aluminum poles, pedestals, and posts shall meet the color requirements as specified in the Contract Documents. All paint systems shall possess physical properties and handling characteristics that are compatible with the application requirements of Section 646. Materials shall be specifically intended for use over aluminum. Paint systems shall exhibit no loss of adhesion or total color difference ( $\Delta E^*_{ab}$ ) greater than 8.0 units for five years after final acceptance as specified in 5-11. An aluminum pole, pedestal, post, or sign panel that exhibits a cumulative surface area of delamination in excess of 50 square inches will constitute an adhesion failure. Delamination shall be defined as any area of exposed metal surface subsequent to hand tool cleaning. A  $\Delta E^*_{ab}$  value exceeding 8.0 units per the International Commission on Illumination L\*a\*b\* 1976 (CIELAB) space and color difference formula, measured in accordance with ASTM D2244, will constitute a color retention failure.

The Department will measure and enter in the Department's database the CIELAB color chromaticity coordinates for the color of the top coat of sample coupons provided as required by 646-2.7 using a BYK-Gardner Handicolor colorimeter using D65 illuminant and 2-degree geometry settings. The Department-measured CIELAB chromaticity coordinates shall define the initial color and will be used for resolution of color retention failures and the resolution of color retention disputes.

#### 965-4 Certification.

Produce a certificate of compliance for non-APL products, upon request of the Engineer. Certificates of compliance shall identify the reportable properties of Table 965-1.