

**BITUMINOUS MATERIALS – FUEL RESISTANT ASPHALT.**  
**(REV 6-23-21)**

SECTION 916 is deleted and the following substituted for locations of fuel resistant asphalt structural and/or friction course as delineated in the Plans. DEV916FRA does not apply for any other structural or friction courses delineated in the Plans.

**SECTION 916**  
**BITUMINOUS MATERIALS – FUEL RESISTANT ASPHALT**

**916-1 General.**

All products supplied under this Specification shall be one of the products included on the Approved Product List (APL). Producers seeking evaluation of a product for inclusion on the APL shall submit an application in accordance with Section 6. Fuel Resistant (FR) binder, PG 88-22 (FR), will not need to be included on the APL, however, a sample of the binder must be tested and approved by the State Materials Office prior to use on the project.

Any marked variation from the original test values for a material below the established limits or evidence of inadequate quality control or field performance of a material will be considered sufficient evidence that the properties of the material have changed, and the material will be removed from the APL.

**916-2 Superpave PG Asphalt Binder:**

**916-2.1 Requirements:** Superpave Performance Graded (PG) asphalt binders, identified as PG 52-28, PG 58-22, PG 67-22, polymer modified asphalt (PMA) binders, PG 76-22 (PMA) and High Polymer, Fuel Resistant (FR) binder, PG 88-22 (FR), and asphalt rubber binders (ARB), PG 76-22 (ARB), shall meet the requirements of 916-2 and AASHTO M 332-20. When the Contract Documents specify either a PG 76-22 (PMA), PG 76-22 (ARB), or PG 76-22 binder, either binder can be used interchangeably at no additional cost to the Department. All PG asphalt binders shall meet the following additional requirements:

1. The intermediate test temperature at 10 rad/sec. for the Dynamic Shear Rheometer (DSR) test (AASHTO T 315-20 shall be 26.5°C for PG grades PG 67 and higher.
2. An additional high temperature grade of PG 67 is added for which the high test temperature at 10 rad/sec for the DSR test (AASHTO T 315-120 shall be 67°C.
3. All PG asphalt binders having a high temperature designation of PG 67 or lower shall be prepared without modification.
4. All PMA and FR binders having a high temperature designation higher than PG 67 shall only be produced with a styrene-butadiene-styrene (SBS) or styrene-butadiene (SB) elastomeric polymer modifier and the resultant binder shall meet all requirements of this Section.
5. Polyphosphoric acid may be used as a modifier not exceeding 0.75% by weight of asphalt binder for PG 76-22 (PMA) and PG 76-22 (ARB) binders. Polyphosphoric acid may not be used in High Polymer binder or PG 88-22 (FR) binder.
6. PG 76-22 (ARB) shall meet the additional requirements of 916-2.1.1.
7. All PG asphalt binders having a high temperature designation of PG 67 or lower shall not have a high temperature true grade more than 5.9°C higher than the specified PG grade, (for example, if a PG 58-22 is specified, do not supply a PG 64-22 or higher).

8. The use of waste oil is prohibited in the modification of any PG binder grade. Waste oil shall be defined as recycled oil products that have not been processed through a vacuum tower and have an initial boiling point of 385°C (725°F) or lower when tested in accordance with ASTM D6352-19.

9. Re-refined engine oil bottoms (REOB)/vacuum tower asphalt extenders (VTAE) may be used as a modifier not exceeding 8.0% by weight of asphalt binder. REOB/VTAE are materials as defined in Asphalt Institute document IS-235.

10. Additional polymer modifiers may be used in the PG 88-22 (FR) binder.

For all PG binder used in all hot mix asphalt, silicone may be added to the PG binder at the rate of 25 cubic centimeters of silicone mixed to each 5,000 gallons of PG binder. If a dispersing fluid is used in conjunction with the silicone, the resultant mixture containing the full 25 cubic centimeters of silicone shall be added in accordance with the manufacturer's recommendation. The blending of the silicone with the PG binder shall be done by the supplier prior to the shipment. When the asphalt binder will be used with a foaming warm mix technology, refer to the technology supplier's guidance on the addition of silicone.

Where an anti-strip additive is required, the anti-strip additive shall meet the requirements of 916-4. The anti-strip additive shall be introduced into the PG binder by the supplier during loading.

**916-2.1.1 Additional Requirements for PG 76-22 (ARB):** The following additional requirements apply only to PG 76-22 (ARB):

1. The asphalt binder shall contain a minimum of 7.0% ground tire rubber (GTR) by weight of asphalt binder.
2. The GTR shall meet the requirements of Section 919.
3. Polymer modification is optional for PG 76-22 (ARB).

**916-2.1.2 High Polymer Binder Blending:** Existing high polymer binder may be blended in an asphalt producer's storage tank to make a PG 76-22 binder provided the following requirements are met:

1. Notify the State Materials Office (SMO) and the local District Materials Office prior to blending.
2. Follow the blending instructions of the high polymer binder supplier.
3. Submit a sample of the blended binder to a SMO approved laboratory for testing. Provide test results to the SMO.
4. Use the newly blended binder only after approval from the SMO.

**916-2.2 Compliance with Materials Manual:** Producers of Superpave PG binders shall meet the requirements of Section 3.5, Volume II of the Department's Material Manual, which may be viewed at the following URL:

<https://www.fdot.gov/programmanagement/Implemented/URLinSpecs/Section35V2.shtm>.

**916-2.3 Reporting:** Specification compliance testing results shall be reported for the tests in Table 916-1 below, unless noted otherwise. Quality control (QC) testing results shall be reported for original binder DSR (G/sin  $\delta$  and phase angle, as applicable).

Table 916-1		
SUPERPAVE PG ASPHALT BINDER		
Test and Method	Conditions	Specification Minimum/Maximum Value
Superpave PG Asphalt Binder Grade		Report
APL Number		Report
Modifier (name and type)	Polymer, Ground Tire Rubber with Approved Product List (APL) number, Sulfur, PPA, REOB, and any Rejuvenating Agents	Report
Original Binder		
Solubility, AASHTO T 44-14 (2018)	in Trichloroethylene	Minimum 99.0% (Not applicable for PG 76-22 (ARB))
Flash Point, AASHTO T 48-18	Cleveland Open Cup	Minimum 450°F
Rotational Viscosity, AASHTO T 316-19	275°F	Maximum 3 Pa·s <sup>(a)</sup>
Dynamic Shear Rheometer <sup>(b)</sup> , AASHTO T 315-20	$G^*/\sin \delta$	Minimum 1.00 kPa
	Phase Angle, $\delta$ <sup>(c)</sup> PG 76-22 (PMA) and PG 76-22 (ARB) <sup>(d)</sup> PG 88-22 (FR)	Maximum 75 degrees Maximum 70 degrees
Separation Test, ASTM D7173-20 and Softening Point, AASHTO T 53-09 (2018)	163±5°C	Maximum 15°F (PG 76-22 (ARB) only)
	48 hours	Maximum 7.2°F (PG 88-22 (FR) only)
Rolling Thin Film Oven Test Residue (AASHTO T 240-13 (2017))		
Rolling Thin Film Oven, AASHTO T 240-13 (2017)	Mass Change %	Maximum 1.00
Multiple Stress Creep Recovery, $J_{nr, 3.2}$ AASHTO T 350-19	Grade Temperature (Unmodified binders only)	“S” = 4.50 kPa <sup>-1</sup> max
Multiple Stress Creep Recovery, $J_{nr, 3.2}$ <sup>(d, e, f)</sup> AASHTO T 350-19	67°C (Modified binders only)	“V” = 1.00 kPa <sup>-1</sup> max Maximum $J_{nr, diff}$ = 75%
	76°C (High Polymer binder only)	0.10 kPa <sup>-1</sup> max
Multiple Stress Creep Recovery, % Recovery <sup>(d, e)</sup> AASHTO T 350-19	67°C (Modified binders only)	$\%R_{3.2} \geq 29.371 (J_{nr, 3.2})^{-0.2633}$
	76°C (High Polymer binder only)	$\%R_{3.2} \geq 90.0$

Table 916-1		
SUPERPAVE PG ASPHALT BINDER		
Elastic Recovery ASTM D6084-18	25°C	Minimum 85.0% (PG 88-22 (FR) only)
Pressure Aging Vessel Residue (AASHTO R 28-12 (2016))		
Dynamic Shear Rheometer, AASHTO T 315-20	$G^* \sin \delta$ , 10 rad/sec.	Maximum 6,000 kPa <sup>(g, h)</sup>
Creep Stiffness, AASHTO T 313-20	S (Stiffness), @ 60 sec. m-value, @ 60 sec.	Maximum 300 MPa Minimum 0.300
$\Delta T_c$ , ASTM D7643-16	20 hours PAV aging S (Stiffness), @ 60 sec. m-value, @ 60 sec.	$\Delta T_c \geq -5.0^\circ\text{C}$
<p>(a) Binders with values higher than 3 Pa·s should be used with caution and only after consulting with the supplier as to any special handling procedures, including pumping capabilities.</p> <p>(b) Dynamic Shear Rheometer (AASHTO T 315-20) shall be performed on original binders for the purposes of QC testing only. The original binder <math>G^*/\sin \delta</math> shall be performed at grade temperature. Grade temperature for High Polymer binder is 76°C.</p> <p>(c) The original binder phase angle (AASHTO T 315-20) shall be performed at grade temperature.</p> <p>(d) AASHTO T 315-20 and AASHTO T 350-20 will be performed at a 2-mm gap for PG 76-22 (ARB).</p> <p>(e) All binders with a high temperature designation &gt;67 will be tested at 67°C. PG 76-22 (PMA) and PG 76-22 (ARB) shall pass a “V” grade and PG 88-22 (FR) shall pass an “E” grade per AASHTO M 332-20.</p> <p>(f) A maximum Jnr diff = 75% does not apply for any Jnr value <math>\leq 0.50</math> kPa-1.</p> <p>(g) For <math>5000 \text{ kPa} \leq G^* \sin \delta \leq 6000 \text{ kPa}</math>, the phase angle, <math>\delta</math>, shall be a minimum of 42°.</p> <p>(h) For PG 67 or higher grades, perform the PAV residue testing at 26.5°C.</p>		

### 916-3 Asphalt Emulsions.

**916-3.1 Compliance with Materials Manual:** Producers of asphalt emulsions shall meet the requirements of Section 3.4, Volume II of the Department’s Material Manual, which may be viewed at the following URL:

<https://www.fdot.gov/programmanagement/Implemented/URLinSpecs/Section34V2.shtm>.

**916-3.2 Requirements:** Use a prime coat meeting the requirements of AASHTO M 140-20 for anionic emulsions, AASHTO M 208-18 or AASHTO M 316-19 for cationic emulsions, or as specified in the Producer’s QC Plan. For anionic emulsions, the cement mixing test will be waived. For tack products, the minimum testing requirements shall include percent residue, naphtha content (as needed), one-day storage stability, sieve test, Saybolt Furol viscosity, original DSR, and solubility (on an annual basis). Residue testing shall be performed on residue obtained from distillation, AASHTO T 59-16 or low- temperature evaporation, AASHTO R 78-16 (2020).

At the direction of the Engineer, sample tack from the distributor used on the project at a minimum frequency of once per project per product. The sample shall be tested by the Department for the following specified material properties: percent residue, contaminants, and the residue property  $G^*/\sin \delta$ . Should any of the test results fail the specification requirements, the tack material will be considered defective and shall not to be used on Department projects unless waived by the Engineer. The Engineer may require the Contractor to obtain roadway cores for bond strength testing (FM 5-599).

**916-4 Liquid Anti-strip Agents.**

**916-4.1 Requirements:** Liquid anti-strip agents shall be tested by the Department in accordance with FM 1-T 283. A minimum tensile strength ratio of 0.80 must be obtained when testing the liquid anti-strip with various aggregate sources and two nominal maximum aggregate size mixtures for approval to be placed on the APL.

**916-4.2 Mix Design Verification:** Particular aggregate sources may require moisture susceptibility testing per FM 1-T 283 for each mix design. Results from this testing may meet the Department's requirement of minimum tensile strength ratio of 0.80 or may indicate the need for a larger dosage rate of anti-strip agent (up to 0.75% maximum) or may require a different anti-strip agent to meet the specification requirements.

Do Not Use Without  
CO Specs Authorization