

204 GRADED AGGREGATE BASE.
(REV 10-31-01) (FA 1-3-02) (7-02)

ARTICLE 204-6 (Page 186) is deleted and the following substituted:

204-6 Compacting and Finishing Base.

204-6.1 General: Meet the requirements of 200-7.1 with density requirements of 204-6.3.

204-6.1.1 Single-Course Base: Construct as specified in 200-6.1.1.

204-6.1.2 Multiple-Course Base: Construct as specified in 200-6.1.2.

204-6.2 Moisture Content: Meet the requirements of 200-6.2.

204-6.3 Density Requirements: After attaining the proper moisture conditions, uniformly compact the material to a density of not less than 100% of the maximum density as determined by FM 1-T 180. Ensure that the minimum density that will be acceptable at any location outside the traveled roadway (such as intersections, crossovers, turnouts, etc.) is 98% of the maximum density.

204-6.4 Density Tests: Meet the requirements of 200-6.4.

204-6.5 Correction of Defects: Meet the requirements of 200-6.5.

204-6.6 Dust Abatement: Minimize the dispersion of dust from the base material during construction and maintenance operations by applying water or other dust control materials.

ARTICLE 204-7 (Page 186) is deleted and the following substituted:

204-7 Testing Surface.

Test the surface in accordance with the requirements of 200-6.