

**200 ROCK BASE-PRIMING.**  
**(REV 5-6-04) (FA 6-29-04) (1-05)**

SUBARTICLE 200-8.1 (Page 198) is deleted and the following substituted:

**200-8.1 Priming:** Apply the prime coat only when the base meets the specified density requirements and when the moisture content in the top half of the base does not exceed the optimum moisture of the base material. At the time of priming, ensure that the base is firm, unyielding and in such condition that no undue distortion will occur.