

283 RECLAIMED ASPHALT PAVEMENT BASE – COMPACTING AND FINISHING BASE.

(REV 5-19-03) (FA 5-20-03) (1-04)

ARTICLE 283-4 (Pages 209 and 210) is deleted and the following substituted:

283-4 Compacting and Finishing Base.

283-4.1 General: Meet the requirements of 200-6.1

283-4.1.1 Single-Course Base: Construct as specified in 200-6.1.1.

283-4.1.2 Multiple-Course Base: Construct as specified in 200-6.1.2.

283-4.2 Moisture Content: Meet the requirements of 200-6.2. Ensure that the moisture content at the time of compaction is within 2% of optimum.

283-4.3 Density Requirements: After attaining the proper moisture content, compact the material to a density of not less than 95% of maximum density as determined by FM 1-T 180. Where the width of the base construction is not sufficient to permit use of standard base compaction equipment, perform compaction using vibratory compactors, trench rollers, or other special equipment which will provide the density requirements specified herein.

283-4.4 Density Tests: Meet the requirements of 200-7 with the exception of 200-7.2.1. Within the entire limits of the width and depth of the base, obtain a minimum density in any LOT of 95% of the maximum density as determined by FM 1-T 180.

283-4.5 Thickness Requirements: Meets the thickness requirements of 285-6.