

300 PRIME AND TACK COATS FOR BASE COURSES.
(REV 5-6-04) (FA 6-29-04) (1-05)

SUBARTICLE 300-7.1 (Page 218) is deleted and the following substituted:

300-7.1 General: Clean the surface to be primed and ensure that the moisture content of the base does not exceed the optimum moisture. Ensure that the temperature of the prime material is between 100 and 150°F [40 and 65°C]. The Engineer will designate the actual temperature to ensure uniform distribution. Apply the material with a pressure distributor. Determine the application amount based on the character of the surface. Use an amount sufficient to coat the surface thoroughly and uniformly with no excess.