

EXPECTED IMPLEMENTATION JANUARY 2006

400 CONCRETE STRUCTURES – FINISHING CONCRETE. (REV 4-12-05) (FA 5-24-05) (1-06)

SUBARTICLE 400-15.2.5.1 (Pages 353-354) is deleted and the following substituted:

400-15.2.5 Class 4 Deck Finish:

400-15.2.5.1 General: Apply a Class 4 finish on bridge decks and concrete approach slabs. On Short Bridges (bridges and approach slabs having a combined length less than or equal to 100 ft [33 m]), and on Miscellaneous Bridges (Pedestrian, Trail, and Movable Spans) regardless of length, meet the finish and smoothness requirements of 400-15.2.5.2 and 400-15.2.5.4. On Long Bridges (bridges and approach slabs having a combined length greater than 100 ft [33 m]) meet the finish and smoothness requirements of 400-15.2.5.3 and 400-15.2.5.5. After meeting the screeding requirements of 400-7.13 and curing requirements of 400-16 and the smoothness requirements, herein, groove the bridge deck and approach slabs.

Regardless of bridge length, finish decks with less than 2-1/2 inches [64 mm] of top cover in accordance with the requirements for Short Bridges.