

**320 HOT BITUMINOUS MIXTURES-COLD FEED.  
(REV 11-3-04) (FA 1-3-05) (7-05)**

SUBARTICLE 320-2.4 (Page 223) is deleted and the following substituted:

**320-2.4 Cold Feed:** Provide a separate cold bin for each component of the fine and coarse aggregates required by the design mix. Equip the cold bins with accurate mechanical means for feeding the aggregates uniformly into the dryer in the proportions required for the finished mix to maintain uniform production and temperature. When using RAP as a component material, use a grizzly or grid over the RAP cold bin, in-line roller crusher, screen, or other suitable means to prevent oversized RAP material from showing up in the completed recycled mixture. If oversized RAP material appears in the completed recycled mix, take the appropriate corrective action immediately. If the appropriate corrective actions are not immediately taken, stop plant operations.