

**970 RAISED RETRO-REFLECTIVE PAVEMENT MARKERS-IN-SERVICE
MINIMUM REFLECTIVE INTENSITY.
(REV 5-2-06) (FA 7-24-06) (1-07)**

SUBARTICLE 970-1.3.3 (Page 861) is deleted and the following substituted:

970-1.3.3 In-service Minimum Reflective Intensity: The Class B reflective pavement marker shall retain a minimum coefficient of luminous intensity for 18 months of not less than 30% of the values shown in Table 1 of ASTM D 4280, and a minimum luminous intensity of 0.2 cd/fc at the end of two years.