

300 MATERIALS-TACK COAT.
(REV 7-26-06) (FA 9-25-06) (7-07)

SUBARTICLE 300-2.3 (Pages 231 and 232) is deleted and the following substituted:

300-2.3 Tack Coat: Unless the Contract Documents call for a specific type or grade of tack coat, use RA-500 meeting the requirements of 916-2, heated to a temperature of 250 to 300°F or undiluted Emulsified Asphalt Grades RS-1, RS-2, CRS-1h, or NTSS-1hm meeting the requirements of 916-4. Heat RS-1, RS-2, CRS-1h, and NTSS-1hm to a temperature of 150 to 180°F. The Contractor may use RS-1 modified to include up to 3% naphtha to improve handling of the material during the winter months.

For night paving, use RA-500 tack coat. The Engineer may approve RS-1, RS-2, CRS-1h, or NTSS-1hm for night paving if the Contractor demonstrates, at the time of use, that the emulsion will break to allow paving in a timely manner.