

520 CURING-MEMBRANE CURING COMPOUND METHOD.
(REV 4-18-07) (FA 4-25-07) (1-08)

SUBARTICLE 520-8.3 (Page 585) is deleted and the following substituted:

520-8.3 Membrane Curing Compound Method: Apply clear membrane curing compound or white pigmented curing compound, as specified in 925-2, by a hand sprayer meeting the requirements of 350-3.10, in a single coat continuous film at a uniform coverage of at least one gallon per 200 square feet. Immediately recoat any cracks, checks, or other defects appearing in the coating. Thoroughly agitate the curing compound in the drum prior to application, and during application as necessary to prevent settlement of the pigment.