

**970 MATERIALS FOR RAISED RETRO-REFLECTIVE PAVEMENT MARKERS
AND BITUMINOUS ADHESIVE.**

(REV 4-13-07) (FA 4-16-07) (1-08)

SUBARTICLE 970-1.3.1 (Page 861) is deleted and the following substituted:

970-1.3.1 Class A Markers: Meet the coefficient of luminous intensity requirements of ASTM D 4280. Abrasion treatment is not required for Class A Markers.

SUBARTICLE 970-1.3.2 (Page 861) is deleted and the following substituted:

970-1.3.2 Class B (Abrasion Resistant) Markers: Meet the coefficient of luminous intensity requirements of ASTM D 4280 after abrasion. Each marker shall be marked as abrasion resistant by the manufacturer.

SUBARTICLE 970-1.3.3 (Page 861) is deleted and the following substituted:

970-1.3.3 In-service Minimum Reflective Intensity: The Class B reflective pavement marker shall retain a minimum coefficient of luminous intensity for 18 months of not less than 30% of the values shown in Table 1 of ASTM D 4280, and a minimum luminous intensity of 0.2 cd/fc at the end of two years.