



## Florida Department of Transportation

**CHARLIE CRIST**  
GOVERNOR

605 Suwannee Street  
Tallahassee, FL 32399-0450

**STEPHANIE KOPELOUSOS**  
SECRETARY

June 10, 2008

Dr. Leslie McCarthy, PhD, P.E.  
Program Operations Engineer  
Federal Highway Administration  
545 John Knox Road, Suite 200  
Tallahassee, Florida 32303

Re: Office of Design, Specifications  
Section 288  
Proposed Specification: 2880700.D01 – Cement Treated Permeable Base

Dear Dr. McCarthy:

We are submitting, for your approval, two copies of the above referenced Supplemental Specification.

Tom Malerk of the State Materials Office proposed this change to provide an acceptability range for unit weight.

Please review and transmit your comments, if any, within four weeks. Comments should be sent via Email to ST986RP or rudy.powell@dot.state.fl.us.

If you have any questions relating to this specification change, please call Rudy Powell, State Specifications Engineer at 414-4110.

Sincerely,

Rudy Powell, Jr., P.E.  
State Specifications Engineer

RP/sh

Attachment

cc: Gregory Jones, General Counsel  
Florida Transportation Builders' Assoc.  
State Construction Engineer  
Marvin Williams, Federal Highway Administration

**288 — CEMENT TREATED PERMEABLE BASE.**

———(~~REV 3-18-083-26-086-10-08~~)

ARTICLE 288-7 (Page 228) is deleted and the following substituted:

**288-7 Sampling and Testing.**

The Engineer will take random samples of the Cement Treated Permeable Base at the point of placement in accordance with FM 5-530 to determine the unit weight. Cement Treated Permeable Base not ~~meeting~~ *within  $\pm 3 \text{ lbs/ft}^3$*  of the unit weight requirement ~~from~~ *of the approved mix design* will be rejected.

Remove, and replace all rejected Cement Treated Permeable Base at no cost to the Department.

**CEMENT TREATED PERMEABLE BASE.**

**(REV 6-10-08)**

ARTICLE 288-7 (Page 228) is deleted and the following substituted:

**288-7 Sampling and Testing.**

The Engineer will take random samples of the Cement Treated Permeable Base at the point of placement in accordance with FM 5-530 to determine the unit weight.

Cement Treated Permeable Base not within  $\pm 3$  lbs/ft<sup>3</sup> of the unit weight of the approved mix design will be rejected.

Remove, and replace all rejected Cement Treated Permeable Base at no cost to the Department.