

EXPECTED IMPLEMENTATION JANUARY 2009

300 MATERIALS-TACK COAT. (REV 6-24-08) (FA 6-30-08) (1-09)

SUBARTICLE 300-2.3 (Pages 231 and 232) is deleted and the following substituted:

300-2.3 Tack Coat: Unless the Contract Documents call for a specific type or grade of tack coat, use RA-500 meeting the requirements of 916-2, heated to a temperature of 250 to 300°F or undiluted Emulsified Asphalt Grades RS-1h, RS-2, CRS-1h, or NTSS-1hm meeting the requirements of 916-4. Heat RS-1h, RS-2, CRS-1h, and NTSS-1hm to a temperature of 150 to 180°F. The Contractor may use RS-1h modified to include up to 3% naphtha to improve handling of the material during the winter months of December, January and February or at any other time, as approved by the Engineer.

For night paving, use RA-500 tack coat. The Engineer may approve RS-1h, RS-2, CRS-1h, or NTSS-1hm for night paving if the Contractor demonstrates, at the time of use, that the emulsion will break and not affect the progress of the paving operation.