

EXPECTED IMPLEMENTATION JULY 2009

D

**446 EDGEDRAIN (DRAINCRETE).
(REV 5-5-08) (FA 10-8-08) (7-09)**

ARTICLE 446-2 (Page 438) is deleted and the following substituted:

446-2 Materials.

Meet the following requirements:

- Portland Cement ConcreteSection 347*
- Coarse Aggregate.....Section 901
- Portland Cement.....Section 921
- Water.....Section 923
- Polyvinyl-Chloride Pipe.....Section 948
- Polyethylene Pipe.....Section 948
- Filter Fabric.....Section 985

*For Draincrete, the concrete requirements of Section 347 are modified as

follows:

Use Type I or II portland cement (no fly ash or other pozzolans permitted).

Composition:

- Grade of coarse aggregate (stone).... #57, #67 or #89
- Maximum Water/Cement ratio0.38
- Minimum cement factor..... 385 lb/yd³ of Draincrete
- Maximum Slump Range Not Applicable
- Fine Aggregate..... None
- Admixtures..... None

Do not use materials which contain hardened lumps, crusts, or frozen matter, or are contaminated with dissimilar material.

R

A

F

T