

ORIGINATION FORM

THE INFORMATION BELOW IS TO BE PROVIDED BY THE ORIGINATOR

Specification: 973

Subject: Structural Plastics

Origination date: January 16, 2009

Originator: Jerry Hocking

Office/Phone: State Structures Office/414-4268

Problem statement: The previous specification was derived from a developmental specification that referenced some ASTM testing that was for wood products. Since that time ASTM has included tests that are for plastic products. Due to the different tests the test results have also changed.

Proposed solution: The revised specification includes the most recent ASTM test procedures that are applicable to plastic products along with relevant test results that reflect actual plastic product testing.

Information source: A QPL submittal from Trelleborg in which their Engineer researched the ASTM Standard tests to determine the appropriate test for each of the required properties. Their submitted results are representative of the plastic properties we are looking for.

Recommended Usage Note:

Estimated fiscal impact, if implemented: A more accurate and current representative ASTM testing methods and test results.

Implementation of these changes, if and when approved, will begin with the January 2010 letting.



Florida Department of Transportation

CHARLIE CRIST
GOVERNOR

605 Suwannee Street
Tallahassee, FL 32399-0450

STEPHANIE KOPELOUSOS
SECRETARY

MEMORANDUM

DATE: February 12, 2009
TO: Specification Review Distribution List
FROM: Rudy Powell, Jr., P.E., State Specifications Engineer
SUBJECT: Proposed Specification: 9730000, Structural Plastics

In accordance with Specification Development Procedures, we are sending you a copy of a proposed specification change.

This change was proposed by Jerry Hocking of the State Structures Office to include the most recent ASTM test procedures applicable to plastic products along with relevant test results that reflect actual plastic product testing.

Please share this proposal with others within your responsibility. Review comments are due within four weeks and should be sent to Mail Station 75 or to my attention via e-mail at ST986RP or rudy.powell@dot.state.fl.us. Comments received after March 12, 2009 may not be considered. Your input is encouraged.

RP/dr
Attachment

STRUCTURAL PLASTICS.
(REV 2-5-09)

SECTION 973 (of the Supplemental Specifications) is deleted and the following substituted:

SECTION 973
STRUCTURAL PLASTICS

973-1 Description.

This work covers structural plastic (SP) components including fiberglass structurally reinforced composite piles (CP), fiberglass structurally reinforced composite lumber (SCL) and smaller dimensional fiberglass fiber reinforced composite lumber (FFRCL).

973-2 Product Acceptance.

Use only products listed on the Department's Qualified Products List (QPL). Manufacturers seeking evaluation of products must submit an application in accordance with Section 6 and include independently certified test reports that the material meets the requirements of this Section.

In accordance with Section 6, provide manufacturer's certification that the material meets the requirements of this section.

973-3 Materials.

Use polyethylene made from recycled post consumer or post industrial thermoplastics. Mix the plastic with appropriate colorants, UV inhibitors, hindered amine light stabilizers and antioxidants so that the resulting product meets the material property requirements specified in Tables 1 and 2. Structural Plastic must not corrode, rot, warp, splinter or crack. The outer skin must be smooth and black in color unless otherwise specified in the Contract Documents.

Manufacture Structural Plastic as one continuous piece with no joints or splices to the dimensions and tolerances in accordance with Table 3 and consisting of a dense outer skin surrounding a less dense core. Interior voids shall not exceed 3/4 inch in diameter. Structural Plastic shall be free of twist and curvature.

Reinforce 10"x10" fiberglass structurally reinforced composite lumber for use in heavy duty and medium duty fender systems with a minimum of four 1 1/2 inch *fiberglass structurally* reinforcing rods placed in the corners of the section. Reinforce 10"x10" fiberglass structurally reinforced composite lumber for use in light duty fender systems with a minimum of four 1 inch *fiberglass structurally* reinforcing rods placed in the corners of the section. Reinforce 16" O.D. Components including fiberglass structurally reinforced composite piles for use in heavy duty fender systems with a minimum of sixteen 1 1/2 inch fiberglass reinforcing rods. Reinforce 16" O.D. Components including fiberglass structurally reinforced composite piles for use in medium duty fender systems with a minimum of sixteen 1 inch fiberglass reinforcing rods.

Reinforcing rods must be continuous and offer a minimum flexural strength of 70.0 ksi when tested in accordance with ASTM D 4476 and a minimum compressive strength of 40.0 ksi when tested in accordance with ASTM D 695. Steel reinforcing rods are not permitted.

Reject any sections of structural plastic containing cracks or splits. Also, inspect the ends of the reinforcing rods and reject any sections containing reinforcing rods with voids or cracks.

Add a minimum of 15% (by weight) chopped fiberglass reinforcement to the polyethylene used for fiberglass structurally reinforced composite lumber, a minimum of 5% (by weight) chopped fiberglass reinforcement for components including fiberglass structurally reinforced composite piles and a minimum of 15% (by weight) chopped fiberglass reinforcement for smaller dimensional fiberglass fiber reinforced composite lumber. The fiberglass reinforcement may be reduced when other means of controlling cracking are specified with test results which show long term cracking is nonexistent.

Fiberglass structurally reinforced composite lumber must meet the minimum structural properties listed in Tables 4A and 4B.

Smaller dimensional fiberglass fiber reinforced composite lumber must meet the minimum physical properties listed in Table 5.

Components including fiberglass structurally reinforced composite piles must meet the structural properties listed in Tables 6A and 6B.

Table 1 Plastic Material Properties- CP and SCL			
Density	ASTM D792	Skin	55-63 pcf
Density	ASTM E12 <i>D792</i>	Core	34-48- 48 - 56 pcf
Water Absorption	ASTM D570		
		Skin	2 hrs:<1.0% weight increase 24 hrs:<3.0% weight increase
Brittleness	ASTM D746	Skin	No break at -40°F at 5 ft lbs/in <i>Brittleness temperature to be less than -40 deg. C</i>
Impact Resistance	ASTM D746 256 Modified <i>Method A (Izod)</i>	Skin	Greater than 4 <i>0.55</i> ft-lbs/in
Hardness	ASTM D2240	Skin	44-75 (Shore D)
Ultraviolet	ASTM D4329 (B-Lamp) <i>UVA</i>	Skin	500 hours<10% change in Shore D Durometer Hardness
		Core	500 hours<10% change in Shore D Durometer Hardness
Abrasion	ASTM D4060	Skin	Weight Loss: <0.02 oz Wear Index: 2.5 to 3.0 Cycles=10,000 Wheel=CS17 Load-2.2 lb
Chemical Resistance	ASTM D543 756	Skin/Core Sea Water Gasoline No. 2 Diesel	<1.5% weight increase <7.5 <i>9.5</i> % weight increase <6.0% weight increase
Tensile Properties	ASTM D638	Skin /Core	Minimum 500 <i>2200</i> psi at break
Compressive Modulus	ASTM D695	Skin /Core	Minimum 40 ksi
Static Coefficient of Friction	ASTM F489-03 <i>D1894</i>		Maximum 0.25, wet
Nail Pull-Out	ASTM D1761	Skin/Core	Minimum 60 lb

	6117		
--	------	--	--

Density	ASTM D6111 792	50-65 pcf
Brittleness	ASTM D746	No break at 40°F at 5 ft lbs/in
Impact Resistance	ASTM D746 Modified D6110	Greater than 4 2.0 ft-lbs/in
Hardness	ASTM D2240	44-75 (Shore D)
Ultraviolet	ASTM D4329 (B-Lamp <i>UVA</i>)	500 hours <10% change in Shore D Durometer Hardness
Abrasion	ASTM D4060	Weight Loss: <0.02 oz Wear Index: 2.5 to 3.0 Cycles = 10,000 Wheel = CS17 Load -2.2 lb
Chemical Resistance	ASTM D543 D756 Sea Water Gasoline No. 2 Diesel	<1.5% weight increase <7.5% weight increase <6.0% weight increase
Tensile Properties	ASTM D638	Minimum 3000 psi at break
Static Coefficient of Friction	ASTM C1028 (Neolite-wet) <i>D2394</i>	Minimum 0.50 .25 , wet or dry
Nail Pull-Out	ASTM D 1761 6117	Minimum 250 lb
Screw Withdrawal	ASTM D6117	Minimum 450 400 lb

Structural Plastic	Dimension	Tolerance
Length	Per order (80 ft Maximum)	0/+6 inch
Width	See Contract Plans	±1/4 inch
Height	See Contract Plans	±1/4 inch
Corner Radius – SCL	1 3/4 inch	±1/4 inch
Corner Radius – FFRCL	1/4 inch	±1/16 inch
Outer Skin Thickness	3/16 inch	±1/8
Distance from outer surface to center rebar elements (SCL)	2 inches	±1/4 inch
Distance from outer surface to center rebar elements (CP)	1 3/8 inches	±1/4 inch
Straightness (gap, bend or inside while lying on a flat surface)		<1 1/2 inches per 10 feet

Table 4A

Structural Properties for Heavy Duty and Medium Duty SCL	
Member Size	10 inches x 10 inches
Modulus of Elasticity as derived below	521 ksi
Stiffness, E.I.	4.05E+08 lb-inch ²
Yield Stress in Bending	5.8 ksi
Weight	30-37 lb/ft

Table 4B Structural Properties for Light Duty SCL	
Member Size	10 inches x 10 inches
Modulus of Elasticity as derived below	307 ksi
Stiffness, E.I.	2.39E+08 lb-inch ²
Yield Stress in Bending	3.4ksi
Weight	28-35 lb/ft

Determine the Modulus of Elasticity of a full size specimen by conducting a three point bend test with a load applied in the center of a simply supported 14-foot span, at a deflection rate of 0.25 inch per minute. The Modulus is to be taken at a strain of 0.01 inch per inch, where strain equals (6) x (depth of cross section) x (deflection) / (span length squared) and where Modulus of Elasticity equals (load) x (span length cubed) / [(48) x (deflection) x (moment of inertia)].

Table 5 Properties for FFRCL	
Modulus of Elasticity ASTM D 6109	306,000 psi
Flexural Strength ASTM D 6109	2,500 psi
Compressive Strength ASTM D 6108	1,960 psi
Compressive Strength Parallel to gain ASTM D 6112 695	3,500 psi
Compressive Strength Perpendicular to gain ASTM D 6112 695	700 4500psi

Table 6A Structural Properties for Heavy Duty CP	
Member Size	16 inch O.D.
Modulus of Elasticity as derived below	1,146 ksi
Stiffness, E.I.	3.69E+09 lb-inch ²
Yield Stress in Bending	9.1 ksi
Weight	68-83 lb/ft

Table 6B Structural Properties for Medium Duty CP	
Member Size	16 inch O.D.
Modulus of Elasticity as derived below	622 ksi

Stiffness, E.I.	2.0E+09 lb-inch ²
Yield Stress in Bending	4.9 ksi
Weight	61-74 lb/ft

Determine the modulus of elasticity for composite piles using the following test:

Place a 54-foot long plastic composite marine fender piling of manufacturer's standard commercial type horizontally in a clamping device so that 6 feet of the piling will be firmly fixed and unable to move and the other end simply supported. Gradually apply a vertical (downward) load to a point 12 feet from the simply-supported end. Measure the deflection along the length of the piling at the load point, and 3 equidistant locations. Use the load and deflection data to calculate the flexural modulus of elasticity, maximum outer fiber stress, stiffness (EI), and the bending stress. The flexural modulus of elasticity is calculated by dividing EI by the moment of inertia of the cross section of the product.

Calculate the properties in Tables 6A and 6B utilizing standard elastic beam flexure formulas (as found in references such as Machinery's Handbook; and Formulas for Stress and Strain, by Roark and Young). Report the Stiffness (EI) as the average of the stiffness at all measurement locations, between zero load and half the load corresponding to the specification yield stress. The specified minimum yield stress in bending shall be reached before failure of the product. Calculate the stress at the load point, on the tension side of the plastic composite marine piling.

As stated, conduct the tests on a full-scale product of the specified size. The results of these tests may be extended through engineering calculations, to a product of another size only if the other size has the same or smaller cross section than the tested product. Do not use smaller cross sections to predict the performance of larger cross sections.

Components including fiberglass structurally reinforced composite piles shall exhibit recoverable deflection with not more than a 5% reduction in bending stiffness (EI) when cyclically load tested. Upon request, the manufacturer of the composite piles must provide cyclical, flexural load test results from an independent test laboratory ensuring the tests were conducted under four point load conditions with a minimum 30.5 feet clear span and a minimum 15 feet shear span. They must have also been conducted on a minimum of a 13" O.D. Structural Plastic pile, for a minimum of 200 load cycles with the applied load producing a minimum of 40% of the composite pile's bending moment at yield, as determined by the formula $M = f (I / c)$ where:

M = bending moment at yield (in-lbs)

f = yield stress in bending (lb/in²)

I = moment of inertia of cross-section (in⁴)

c = distance from neutral axis to point where stress is desired (inches)