

**341 ASPHALT RUBBER MEMBRANE INTERLAYER.**  
**(REV 7-29-09) (FA 8-11-09) (1-10)**

ARTICLE 341-4 (Pages 314 and 315) is deleted and the following substituted:

**341-4 Contractor's Quality Control.**

Provide the necessary quality control of the asphalt rubber binder, and interlayer construction in accordance with the Contract requirements. Provide in the Quality Control Plan procedures for monitoring and controlling of rate of application. If the rate of application varies by more than 5% from the rate set by the Engineer in accordance with 341-6, immediately make all corrections necessary to bring the spread rate into the acceptable range. The Engineer may take additional measurements at any time. The Engineer will randomly check the Contractor's measurement to verify the spread rate.

ARTICLE 341-5 (Page 315) is deleted and the following substituted:

**341-5 Preparation of Asphalt Rubber Binder.**

Meet the requirements of Section 336 Asphalt Rubber Binder, particularly noting testing and action requirements to be met at the project site/asphalt plant. Combine the materials as rapidly as possible for such a time and at such a temperature that the consistency of the binder approaches that of a semi-fluid material. The Engineer will be the sole judge of when the material has reached application consistency and will determine if an extender oil or diluent is needed for that purpose. After reaching the proper consistency, proceed with application immediately. Never hold the mixture at temperatures over 350°F for more than six hours after reaching that temperature.