

# EXPECTED IMPLEMENTATION JULY 2010

D

## **710 PAINTED PAVEMENT MARKINGS.** **(REV 1-22-10) (FA 1-25-10) (7-10)**

ARTICLE 710-2 (of the Supplemental Specifications) is deleted and the following substituted:

### **710-2 Materials.**

Use only materials listed on the Qualified Products List (QPL) meeting the following requirements:

Raised Retro-reflective Pavement Markers and Bituminous Adhesive .....	Section 970
Standard Waterborne Fast Dry Traffic Paint .....	971-1 and 971-3
Durable Waterborne Traffic Paint .....	971-1 and 971-4
Glass Spheres .....	971-1 and 971-2

The Engineer will take random samples of all material in accordance with the Department's Sampling, Testing and Reporting Guide schedule.

R

SUBARTICLE 710-4.3 (of the Supplemental Specifications) is deleted and the following substituted:

A

**710-4.3 Retroreflectivity:** Apply white and yellow standard and durable pavement markings that will attain an initial retroreflectance of not less than 300 mcd/lx·m<sup>2</sup> and not less than 250 mcd/lx·m<sup>2</sup>, respectively. Measure, record and certify on a Department approved form and submit to the Engineer, the retroreflectivity of white and yellow pavement markings in accordance with Florida Method FM 5-541.

The Department reserves the right to test the markings within 3 days of receipt of the Contractor's certification. Failure to afford the Department opportunity to test the markings will result in non-payment. The test readings should be representative of the Contractor's striping performance. If the retroreflectivity values measure below values shown above, reapply the striping at no additional cost to the Department.

F

For painted pavement markings, ensure that the minimum retroreflectance of white and yellow pavement markings are not less than 150 mcd/lx m<sup>2</sup>. If the retroreflectivity values fall below the 150 mcd/lx m<sup>2</sup> value within six months of initial application, the striping will be reapplied at the Contractor's expense.

SUBARTICLE 710-4.5 (Page 797) is deleted and the following substituted:

T

**710-4.5 Glass Spheres:** Apply glass spheres on all pavement markings immediately and uniformly following the paint application. For standard paint markings, the type of beads and the rate of application shall be based on the manufacturer's recommendation. For durable paint markings, apply a single drop of Type 3 glass spheres. The rate of application of Type 3 glass spheres shall be based on the manufacturer's recommendation.