

450 PRECAST PRESTRESSED CONCRETE CONSTRUCTION - CONCRETE PLACEMENT.

(REV 6-5-09) (FA 6-10-09) (1-10)

SUBARTICLE 450-10.3.2.3 (Page 484) is deleted and the following substituted:

450-10.3.2.3 All Beams 63 Inches or Deeper: Place concrete in a minimum of three horizontal layers. The thickness of the first layer will be such that the top of the concrete is slightly above the top of the bottom flange. The thickness of the second layer will be such that the top of the concrete is slightly above the bottom of the top flange. Fill the beam forms by the last layer.