

EXPECTED IMPLEMENTATION JANUARY 2011

300 PRIME AND TACK COATS FOR BASE COURSES. (REV 6-10-10) (FA 8-16-10) (1-11)

SUBARTICLE 300-8.4 (of the Supplemental Specifications) is deleted and the following substituted:

300-8.4 Rate of Application: Use a rate of application as defined in Table 300-1. Control the rate of application to be within plus or minus 0.01 gal. per square yard of the target application rate. The target application rate may be adjusted by the Engineer to meet specific field conditions. Determine and record the rate of application a minimum of twice per day, once at the beginning of each day's production and again as needed to control the operation. When using RA-550, multiply the target rate of application by 0.6.

Asphalt Mixture Type	Underlying Pavement Surface	Target Tack Rate (gal/yd ²)
Base Course, Structural Course, Dense Graded Friction Course	Newly Constructed Asphalt Layers	0.02 minimum
	Milled Surface or Oxidized and Cracked Pavement	0.06
	Concrete Pavement	0.08
Open Graded Friction Course	Newly Constructed Asphalt Layers	0.05
	Milled Surface	0.07