

EXPECTED IMPLEMENTATION JANUARY 2011

971 TRAFFIC MARKING MATERIALS. (REV 5-6-10) (FA 5-11-10) (1-11)

SUBSECTION 971-8.3.2 (of the Supplemental Specifications) is deleted and the following substituted:

971-8.3.2 Abrasion Resistance: Test four samples per LOT using a Taber Abrader. The material shall be applied to specimen plates using a drawdown blade having a clearance of 26 mils. Air dry each sample for 30 minutes and bake at 220°F for 18 hours. Clean with a soft brush and weigh each sample. Abrade samples for 1,000 cycles with 500 g weights and CS-10 wheels. Clean the samples with a soft brush and weigh again. The average weight loss for the four plates shall not exceed 50 mg per plate.

D

R

A

F

T