

EXPECTED IMPLEMENTATION JULY 2011

560 COATING STRUCTURAL STEEL. (REV 10-4-10) (FA 11-9-10) (7-11)

SUBARTICLE 560-11.2 (of the Supplemental Specification) is deleted and the following substituted:

560-11.2 Application of Coating: Unless otherwise shown in the Contract Documents, apply the inorganic zinc and coal tar-epoxy coatings to all sides of H piles and the exposed side of sheet and pipe piles from the top of the piles to a depth of five feet below the lower of the design ground surface or the design scour depth. Apply the inorganic zinc in accordance with this Section. Apply the coal tar-epoxy in accordance with the following specific requirements:

(1) Apply the coal tar-epoxy system in two coats. The time interval between the first coat and the second coat will be in strict accordance with the coating manufacturer's published specifications. Apply the first coat to yield a dry film thickness of 8 to 10 mils. Apply the second coat to attain a total dry film thickness of the two coats between 16 and 20 mils.

(2) Ensure that no portion of the coating is less than the specified minimum film thicknesses. The total minimum film thickness for any combination of coats will be the sum total of the averages of the specified thickness range of the individual coats.

(3) After applying the coating on the steel piles, the Engineer will thoroughly inspect the surfaces and make film thickness measurements at the approximate rate of one for each 25 ft² of area unless deficient thickness is found. In this case, the rate of sub-measurements will be increased as required to determine the extent of the deficient area.