

# EXPECTED IMPLEMENTATION JULY 2011

## 971 TRAFFIC MARKING MATERIALS. (REV 2-15-11) (FA 2-22-11) (7-11)

SUBARTICLE 971-4.3.2 (Page 927) is deleted and the following substituted:

**971-4.3.2 Abrasion Resistance:** Test four samples per LOT using a Taber Abrader. The paint shall be applied to specimen plates using a drawdown blade having a clearance of 26 mils. Air dry each sample for 30 minutes and bake at 220°F for 18 hours. Clean with a soft brush and weigh each sample. Abrade samples for 1,000 cycles with 500 g and CS-10 wheels. Clean the samples with a soft brush and weigh again. The average weight loss for the four plates shall not exceed 50 mg per plate.

D

R

A

F

T