

EXPECTED IMPLEMENTATION JANUARY 2012

D

234 SUPERPAVE ASPHALT BASE.
(REV 5-19-11) (FA 8-4-11) (1-12)

ARTICLE 234-4 (Page 219) is deleted and the following substituted:

234-4 Contractor's Process Control.

Meet the requirements of 320-2, 330-2 and 334-4.

R

SUBARTICLE 234-8.1 (Page 220) is deleted and the following substituted:

234-8.1 General: The total thickness of the Type B asphalt layers will be the plan thickness as shown in the Contract Documents. Before paving, propose a thickness for each individual layer meeting the requirements of this specification, which when combined with other layers (as applicable) will equal the plan thickness. For construction purposes, the plan thickness and individual layer thickness will be converted to spread rate based on the maximum specific gravity of the asphalt mix being used, as well as the minimum density level, as shown in the following equation:

$$\text{Spread rate (lbs. per square yard)} = t \times G_{mm} \times 43.3$$

Where: t = Thickness (in.) (Plan thickness or individual layer thickness)

G_{mm} = Maximum specific gravity from the verified mix design

The weight of the mixture shall be determined as provided in 320-3.2. For target purposes only, spread rate calculations should be rounded to the nearest whole number.

A

F

T