

# EXPECTED IMPLEMENTATION JANUARY 2012

## 562 REPAIR OF GALVANIZED SURFACES. (REV 3-2-11) (FA 5-10-11) (1-12)

ARTICLE 562-2 (Page 714) is deleted and the following substituted:

### 562-2 Materials.

**562-2.1 Areas 100 Square Inches or Less:** Use a cold galvanizing compound containing at least 92% zinc dust in the dry film.

**562-2.2 Areas Greater than 100 Square Inches:** Use a galvanizing compound as specified in 975-2.4.1 and listed on the Qualified Products List (QPL).

D

R

A

F

T