

562 REPAIR OF GALVANIZED SURFACES.

(REV 3-2-11) (FA 5-10-11) (1-12)

ARTICLE 562-2 (Page 714) is deleted and the following substituted:

562-2 Materials.

562-2.1 Areas 100 Square Inches or Less: Use a cold galvanizing compound containing at least 92% zinc dust in the dry film.

562-2.2 Areas Greater than 100 Square Inches: Use a galvanizing compound as specified in 975-2.4.1 and listed on the Qualified Products List (QPL).