

EXPECTED IMPLEMENTATION JULY 2012

971 TRAFFIC MARKING MATERIALS. (REV 12-20-11) (FA 1-13-12) 7-12)

SUBARTICLE 971-3.2 (Page 925) is deleted and the following substituted:

971-3.2 Composition:

Component	Test Method	Criteria
Total Solids, by weight	ASTM D 2369	minimum 75%
Pigments, by weight	ASTM D 3723	minimum 57%
Vehicle Solids % of Vehicle*		minimum 40%
TiO ₂ , Type II Rutile (white paint only)	ASTM D 476	minimum 1.0 lb/gal
Volatile Organic Content, (VOC)	ASTM D 3960	maximum 150 g/L

*Vehicle Solids % of Vehicle = $\frac{\% \text{ total solids} - \% \text{ pigment}}{100 - \% \text{ pigment}}$

D

R

A

F

T