

ORIGINATION FORM

Date: May 7, 2012

Originator: Greg Sholar

Contact Information: 352.955.2920; gregory.sholar@dot.myflorida.com

Specification Title: Hot Mix Asphalt-General Construction Requirements

Specification Section, Article, or Subarticle Number: 330

Why does the existing language need to be changed? Continual improvement of the Specification to address Department and Industry needs.

Summary of the changes: 1. Modified Table 330-1 related to air temperature requirements based on mix type and layer thickness. 2. Removed requirement that the Contractor perform rolling straightedge Quality Control testing on friction course layers that are accepted for pavement smoothness by the laser profiler. 3. Specified that only straightedge deficiencies that are "high" can be milled to a depth to fix the deficiency. "Low" deficiencies must be milled full depth of the layer.

Are these changes applicable to all Department jobs? If not, what are the restrictions?

These changes are applicable to all Department jobs.

Will these changes result in an increase or decrease in project costs? If yes, what is the estimated change in costs? No identified increases in project costs.

With who have you discussed these changes? Department and Industry staff.

What other offices will be impacted by these changes? Materials and Construction.

Are changes needed to the PPM, Design Standards, SDG, CPAM or other manual? None that I am aware of.

Is a Design Bulletin, Construction Memo, or Estimates Bulletin needed? No.

Contact the State Specifications Office for assistance in completing this form.

Frances Thomas 850-414-4101 frances.thomas@dot.state.fl.us

Debbie Toole 850-414-4114 deborah.toole@dot.state.fl.us

Andy Harper 850-414-4127 clifton.harper@dot.state.fl.us



Florida Department of Transportation

RICK SCOTT
GOVERNOR

605 Suwannee Street
Tallahassee, FL 32399-0450

ANANTH PRASAD, P.E.
SECRETARY

M E M O R A N D U M

DATE: May 29, 2012

TO: Specification Review Distribution List

FROM: Trey Tillander, State Specifications Engineer

SUBJECT: Proposed Specification: **3300302 Hot Mix Asphalt – General Construction Requirements.**

In accordance with Specification Development Procedures, we are sending you a copy of a proposed specification change.

This change was proposed by Greg Sholar of the State Materials Office to update the language for current Department and Industry practice.

Please share this proposal with others within your responsibility. Review comments are due within four weeks and should be sent to Mail Station 75 or to my attention via e-mail at SP965TT or trey.tillander@dot.state.fl.us. Comments received after **June 27, 2012**, may not be considered. Your input is encouraged.

TT/dt
Attachment

HOT MIX ASPHALT – GENERAL CONSTRUCTION REQUIREMENTS.
(REV 5-7-12)

SUBARTICLE 330-3.2.2 (of the Supplemental Specifications) is deleted and the following substituted:

330-3.2.2 Ambient Air Temperature: Place the mixture only when the air temperature in the shade and away from artificial heat meets requirements of Table 330-1. The minimum ambient temperature requirement may be reduced by 5°F when using warm mix technology, if mutually agreed to by both the Engineer and the Contractor. For ~~friction course~~ *FC-5* mixtures, meet the requirements of 337-7.

| Table 330-1 Ambient Air Temperature Requirements for Paving | |
|---|--------------------------|
| Layer Thickness or Asphalt Binder Type | Minimum Temperature (°F) |
| ≤ 1/2 inch | 50 |
| ≤ 1 inch or any mixture containing a PG asphalt binder having a high temperature designation greater than PG-67 <i>Any mixture > 1 inch containing a PG asphalt binder having a high temperature designation ≥ 76°C or ARB-5</i> | 45 |
| <i>Any mixture > 1 inch containing a PG asphalt binder having a high temperature designation < 76°C</i> | 40 |

SUBARTICLE 330-9.4.2 (of the Supplemental Specifications) is deleted and the following substituted:

330-9.4.2 Test Method: Perform all straightedge testing in accordance with FM 5-509 in the outside wheel path of each lane. The Engineer, ~~may~~ require additional testing at other locations within the lane.

SUBARTICLE 330-9.4.5.1 (of the Supplemental Specifications) is deleted and the following substituted:

330-9.4.5.1 General: Straightedge the final Type SP structural layer and friction course layer in accordance with 330-9.4.2, ~~regardless of whether the method of acceptance is by straightedge or laser profiler~~, *with the exception that if the method of acceptance is by laser profiler, then straightedging of the friction course layer is not required.* Test all pavement lanes and ramps where the width is constant and document all deficiencies in excess of 3/16 inch on a form approved by the Engineer.

SUBARTICLE 330-9.4.5.2 (of the Supplemental Specifications) is deleted and the following substituted:

330-9.4.5.2 Straightedge Exceptions: Straightedge testing will not be required in the following areas: shoulders, intersections, tapers, crossovers, sidewalks, ~~bicycle~~/shared use paths, parking lots and similar areas, or in the following areas when they are less than 250 feet in length: turn lanes, acceleration/deceleration lanes and side streets. The limits of the intersection will be from stop bar to stop bar for both the mainline and side streets.

As an exception, in the event the Engineer identifies a surface irregularity in the above areas that is determined to be objectionable, straightedge and address all deficiencies in excess of 3/8 inch in accordance with 330-9.5.

The Engineer may waive straightedge requirements for transverse joints at the beginning and end of the project, at the beginning and end of bridge structures, at manholes, and at utility structures if the deficiencies are caused by factors beyond the control of the Contractor, as determined by the Engineer. In addition, the Engineer may also waive the straightedging requirements on ramps and superelevated sections where the geometrical orientation of the pavement results in an inaccurate measurement with the rolling straightedge.

SUBARTICLE 330-9.4.5.5 (of the Supplemental Specifications) is deleted and the following substituted:

330-9.4.5.5 Friction Course Layer: *Where required per 330-9.4.5.1,* ~~S~~straightedge the friction course layer in accordance with 330-9.4.2, either behind the final roller of the paving train or as a separate operation upon completion of all paving operations. Notify the Engineer of the location and time of straightedge testing a minimum of 48 hours before beginning testing. The Engineer will verify the straightedge testing by observing the QC straightedging operations. Address all deficiencies in excess of 3/16 inch in accordance with 330-9.5. ~~For laser acceptance, corrections may be made either before or after laser acceptance testing.~~

SUBARTICLE 330-9.5.1.1 (of the Supplemental Specifications) is deleted and the following substituted:

330-9.5.1.1 Structural Layers: Correct all deficiencies, as defined in these Specifications, in the Type SP structural layers by removing and replacing the full depth of the layer, extending a minimum of 50 feet on both sides (where possible) of the defective area for the full width of the paving lane.

As an option, for *high* straightedge deficiencies only, mill the pavement surface *the full lane width* to a depth and ~~width~~*length* that is adequate to remove the deficiency. This option only applies if the structural layer is not the final surface layer.