

EXPECTED IMPLEMENTATION JULY 2013

400 CONCRETE STRUCTURES. (REV 9-5-12) (FA 10-26-12) (7-13)

SUBARTICLE 400-15.2.4 (Page 378) is deleted and the following substituted:

400-15.2.4 Class 3 Surface Finish: Where this surface finish is specified, use forms with a form liner. Where specified or required in the Plans, use No. 89 coarse aggregate for concrete.

After concrete has been placed in the forms and compacted, finish all exposed surfaces which are not contained by the forms to produce a surface texture as nearly equal to that produced by the form as practicable. Generally, finish unformed surfaces to a smooth, dense surface with a steel trowel.

Perform all work, including general surface finish work, in a manner that will preserve the same surface texture and color produced by the form liner. Pointed areas may be rubbed with a dry carborundum stone.

D

R

A

F

T