

EXPECTED IMPLEMENTATION JANUARY 2014

702 WET WEATHER PAVEMENT MARKINGS. (REV 6-7-13) (FA 8-6-13) (1-14)

SUBARTICLE 702-4.2 (Page 839) is deleted and the following substituted:

702-4.2 Thickness and Dimensions of Markings: For flat thermoplastic markings provide a thickness of 0.100 to 0.150 inches when measured above the pavement surface.

As an alternative to the flat baseline, a profiled baseline meeting the following dimensions may be applied. For profiled thermoplastic markings make profile measurements above the pavement surface. Provide a baseline thickness not to exceed 0.050 inches. Provide individual profiles across the full width of the marking on approximately 1.0 inch centers with a space between profiles of approximately .25 inches and an average thickness of at least 0.110 inches above the baseline profile.

Measure, record and certify on a Department approved form and submit to the Engineer, the thickness of white and yellow pavement markings in accordance with FM 5-541.

The Engineer will verify the thickness of the pavement markings in accordance with FM 5-541 within 30 days of receipt of the Contractor's certification.