

3200603 HOT MIX ASPHALT – PLANT METHODS AND EQUIPMENT
COMMENTS FROM INTERNAL/INDUSTRY REVIEW

D3 Materials Office

Comments: (12-16-15)

It is important to keep the minimum temperature of 280F because all of our structural and friction course mixes in District Three use 20% RAP along with PG 76-22 or PG 82-22 liquid asphalt. The +/- 30F from the compaction temperature should be the same for truck measurements and windrow measurements to prevent confusion and errors from happening.

Response:
