

EXPECTED IMPLEMENTATION JULY 2016

287 ASPHALT TREATED PERMEABLE BASE. (REV 10-16-15) (FA 1-26-16) (7-16)

287-2 Materials.

Meet the following requirements:

Coarse Aggregate, Stone, Slag, or Crushed Gravel

Grade No. 57 or 67.....Section 901

Superpave PG Asphalt Binder (PG 67-22) ⁽¹⁾ 916-1

Hydrated Lime ⁽²⁾AASHTO M-303-89 Type 1

Polyvinyl-Chloride Pipe ⁽³⁾Section 948

Polyethylene Pipe ⁽³⁾Section 948

Geosynthetic MaterialSection 985

1. Use PG 67-22 in the ATPB containing 0.75% heat-stable anti-strip additive (by weight of asphalt) from an approved source. Introduce and mix the anti-strip additive at the terminal.

2. For mixtures containing granite, add hydrated lime at a dosage rate of 1.0% by weight of the total dry aggregate in lieu of adding 0.75% anti-strip additive. Submit certified test results for each shipment of hydrated lime indicating compliance with the Specifications. In addition, meet the requirements of 337-9.2 and 337-9.3.

3. Use either polyvinyl chloride pipe or polyethylene pipe, unless otherwise specified in the Contract Documents.