

EXPECTED IMPLEMENTATION JANUARY 2018

204 GRADED AGGREGATE BASE. (REV 4-21-17) (FA 4-27-17) (1-18)

SUBARTICLE 204-6.3 is deleted and the following substituted:

204-6.3 Density Requirements: After attaining the proper moisture conditions, uniformly compact the material to a density of not less than 100% of the maximum density as determined by FM 1-T 180, Method D. For shoulder only areas and shared use paths, obtain a minimum density of 98% of the maximum density as determined by FM 1-T 180, Method D.

SUBARTICLE 204-6.4 is deleted and the following substituted:

204-6.4 Density Tests: Meet the requirements of 200-7.2.2.