

# EXPECTED IMPLEMENTATION JANUARY 2019

## **320 HOT MIX ASPHALT – PLANT METHODS AND EQUIPMENT.** **(REV 5-1-18) (FA 7-5-18) (1-19)**

SUBARTICLE 320-6.2 is deleted and the following substituted:

**320-6.2 Storage:** If necessary, store the asphalt mixture in a surge bin or hot storage silo for a maximum of 72 hours. For FC-5 mixtures containing mineral fibers, store the asphalt mixture in a surge bin or hot storage silo for a maximum of one hour. For FC-5 mixtures containing cellulose fibers, store the asphalt mixture in a surge bin or hot storage silo for a maximum of 1-1/2 hours.

D

R

A

F

T