

EXPECTED IMPLEMENTATION JANUARY 2019

D 337 ASPHALT CONCRETE FRICTION COURSE.
(REV 5-1-18) (FA 7-5-18) (1-19)

SUBARTICLE 337-7.1 is deleted and the following substituted:

337-7.1 Hot Storage of FC-5 Mixtures: When using surge or storage bins in the normal production of FC-5, do not leave mixtures containing mineral fibers in the surge or storage bin for more than one hour. Do not leave mixtures containing cellulose fibers in the surge or storage bin for more than 1-1/2 hours.

R

A

F

T