

9320300 NONMETALLIC ACCESSORY MATERIALS FOR CONCRETE PAVEMENT AND  
CONCRETE STRUCTURES  
COMMENTS FROM INTERNAL/INDUSTRY REVIEW

---

Antonio Nanni

Work Phone: 305-284-3461

nanni@miami.edu

Comments: (6-4-21)

Consider reordering the first two lines in Table 932-6 based on nominal diameter, and clarifying the footnote for distinguishing “large tow grade carbon fiber (257 ksi)” to something more generic, since this is not an industry standard term.

Response:

---

Pete Renshaw

Work Phone: +64-6-867-8582

E-Mail: pete@pultron.com

Comments: (6-10-21)

Table 932-6 (sizes and tensile loads for FRP reinforcing bars): For the #10 bar, the maximum cross-sectional area is listed as 1.385 in<sup>2</sup> - which matches the ASTM standard, D7957. This is fine for a tensile modulus limit of 6500 ksi, as also listed in your standard (and again, matching the ASTM). However, it is known that FDOT are promoting the use of higher modulus rebars in their construction. It is considered unlikely that a bar with this cross-section would achieve the higher modulus requirements. This is currently also under review within the ASTM committee. To achieve the higher modulus (8700 ksi), it appears that 1.473 in<sup>2</sup> will be required, and this number has been put forward at ASTM.

Response: