



Florida Department of Transportation

RON DESANTIS
GOVERNOR

605 Suwannee Street
Tallahassee, FL 32399-0450

JARED W. PERDUE, P.E.
SECRETARY

August 13, 2026

Daniel Holt, PE, PTOE
Director, Project Delivery
Director, Technical Services
FHWA
400 West Washington Street, Suite 4200
Orlando, FL 32801

Re: State Specifications Office
Section: 975
Proposed Specification: **9750600 Structural Coating Materials**

Dear Mr. Holt:

We are submitting, for your approval, two copies of the above referenced Supplemental Specification.

The changes are proposed by Mateo Carvajal to revise the existing language allowing water-repellent coatings as a Class 5 option.

Please review and transmit your comments, if any, within two weeks (10 business days). Comments should be sent via email daniel.strickland@dot.state.fl.us.

If you have any questions relating to this specification change, please call me at (850) 414-4130.

Sincerely,

Signature on File

Daniel Strickland, P.E.
State Specifications Engineer

DS/am

Attachment

cc: Florida Transportation Builders' Assoc.
State Construction Engineer

STRUCTURAL COATING MATERIALS (REV 5-26-26)

ARTICLE 975-1 is deleted and the following substituted:

975-1 General Requirements.

975-1.1 General: Upon curing, all coatings and/or coating systems must produce an adherent coating that is visually uniform. The composition of the coating is left to the discretion of the manufacturer but the finished product shall meet all requirements of this Section. All coats of multi-coat systems shall be supplied by the same manufacturer. Multi-component coatings shall be prepackaged in the required ratios.

975-1.2 Environmental Requirements: Coating materials and their waste shall be characterized as non-hazardous as defined by Resource Conservation and Recovery Act (RCRA) Subarticle C rules, Table 1 of 40 CFR 261.24 Toxicity Characteristic.

Volatile Organic Compounds (VOC) shall be less than 3.5 pounds per gallon when tested in accordance with ASTM D3960.

975-1.3 Approved Product List (APL): , a All materials shall be one of the products listed on the Department's Approved Product List (APL). Manufacturers seeking evaluation of their product shall submit an application in accordance with Section 6 and include the documentation identified in Table 975-1.

Table 975-1 APL Required Documentation	
Documentation	Requirements
Product Photo	Provide product photos that display the significant features of the product.
Technical Data Sheet	Provide product data sheets that uniquely identifies the product and includes product specifications, storage instructions, and recommended installation materials and equipment as applicable.
Product label and Packaging	Materials shall be shipped in containers legibly marked with application instructions, lot number, batch number, date of manufacture, shelf life, and Department APL number. Each lot or batch manufactured must have a unique number.
Safety Data Sheet (SDS)	Provide SDS meeting OSHA requirements for product and manufacturer recommended installation materials as applicable. Non-Hazardous, per RCRA Subtitle C Table 1 of 40 CFR 261.24 "Toxicity Characteristic" and not exude fumes which are hazardous, toxic, or detrimental to persons or property.

Independent Lab Test Report	Provide test reports as required for each product, showing that the product meets this specification. Reports may come from: 1. an independent testing lab, conducted in accordance with the specification requirements. Laboratories used must be independent from the manufacturer unless otherwise stated in the specification. 2. AASHTO Product Evaluation & Audit Solutions Test Report in accordance with the specifications. Testing reports cannot be reused for the same product requalification. Samples for testing reports must be supplied from current production. Product SDS or performance test reports showing percent weight compositional analysis including Chemical Abstract Number, ACGIH time weighted average and ceiling exposure limits for all components, lower and upper explosive limits, flash point, boiling point, amount of volatile organic compounds by weight, and specific gravity for each component of the coating system.
Manufacturer's Instructions	Manufacturer's instructions must include surface preparation details.
Coating Identification	When applicable, the Department will conduct Fourier Transform Infrared Spectroscopy (FTIR) analysis on coating system components for material identification.
Product Sample (for APL listing)	A sample may be requested to verify the product. If the product is a system, a sample of each component must be submitted. Prepare samples in accordance with the product specific requirements of this Section.

ARTICLE 975-6 is deleted and the following substituted:

975-6 Class 5 Applied Finish Coatings.

975-6.1 General: All coatings shall possess physical properties and handling characteristics compatible with the application requirements of Section 400. Unless otherwise specified, the color of the finish coat shall meet SAE Standard AMS-STD-595A, Appendix A – Master Color List, Shade No. 36622, or No. 36642 for uncoated weathering steel bridges. Upon request, submit a one-quart wet sample of each component of each coating system to the SMO.

975-6.2 Textured Finish Coatings: Submit the samples to an independent laboratory for testing. Textured finish coatings shall meet the requirements in Table 975-5.

975-6.3 Water-Repellent Coatings: Submit the samples to an independent laboratory for testing. Water-Repellent coatings shall meet the requirements in Table 975-5 and shall be of water-based silicone acrylic.

Table 975-5
Class 5 Applied Finish Coatings Performance Requirements

Laboratory Testing		
Property	Test Method	Acceptance Criteria
Resistance to Wind Driven Rain	ASTM D6904	No visible water leaks, and if the rear face of the block is damp, the average gain in weight of the three 8"x16"x2" blocks must be less than 0.2 lb.
Freeze Thaw Resistance	AASHTO R 31 Test No. 6	No disbondment
Water Vapor Transmission	ASTM D1653 Method B Condition C	WVT $\geq$ 10 perms
Abrasion Resistance	ASTM D968, 3,000 Liters of Sand	No loss of coating thickness per ASTM D6132
Salt Spray (Fog) Resistance	ASTM B117 2,000 hours	No disbondment
Fluorescent UV-Condensation Exposure	ASTM D4587 2000 hours 4 hours UV 4 hours Condensation	No blistering per ASTM D714. No cracking or delamination. Chalking rating no less than 8 per ASTM D4214 Method D.
Fungal Resistance	ASTM D3273	Rating of 10 per ASTM D3274

STRUCTURAL COATING MATERIALS

(REV 5-26-26)

ARTICLE 975-1 is deleted and the following substituted:

975-1 General Requirements.

975-1.1 General: Upon curing, all coatings and/or coating systems must produce an adherent coating that is visually uniform. The composition of the coating is left to the discretion of the manufacturer but the finished product shall meet all requirements of this Section. All coats of multi-coat systems shall be supplied by the same manufacturer. Multi-component coatings shall be prepackaged in the required ratios.

975-1.2 Environmental Requirements: Coating materials and their waste shall be characterized as non-hazardous as defined by Resource Conservation and Recovery Act (RCRA) Subarticle C rules, Table 1 of 40 CFR 261.24 Toxicity Characteristic.

Volatile Organic Compounds (VOC) shall be less than 3.5 pounds per gallon when tested in accordance with ASTM D3960.

975-1.3 Approved Product List (APL): , a All materials shall be one of the products listed on the Department's Approved Product List (APL). Manufacturers seeking evaluation of their product shall submit an application in accordance with Section 6 and include the documentation identified in Table 975-1.

Table 975-1 APL Required Documentation	
Documentation	Requirements
Product Photo	Provide product photos that display the significant features of the product.
Technical Data Sheet	Provide product data sheets that uniquely identifies the product and includes product specifications, storage instructions, and recommended installation materials and equipment as applicable.
Product label and Packaging	Materials shall be shipped in containers legibly marked with application instructions, lot number, batch number, date of manufacture, shelf life, and Department APL number. Each lot or batch manufactured must have a unique number.
Safety Data Sheet (SDS)	Provide SDS meeting OSHA requirements for product and manufacturer recommended installation materials as applicable. Non-Hazardous, per RCRA Subtitle C Table 1 of 40 CFR 261.24 "Toxicity Characteristic" and not exude fumes which are hazardous, toxic, or detrimental to persons or property.

Independent Lab Test Report	Provide test reports as required for each product, showing that the product meets this specification. Reports may come from: 1. an independent testing lab, conducted in accordance with the specification requirements. Laboratories used must be independent from the manufacturer unless otherwise stated in the specification. 2. AASHTO Product Evaluation & Audit Solutions Test Report in accordance with the specifications. Testing reports cannot be reused for the same product requalification. Samples for testing reports must be supplied from current production. Product SDS or performance test reports showing percent weight compositional analysis including Chemical Abstract Number, ACGIH time weighted average and ceiling exposure limits for all components, lower and upper explosive limits, flash point, boiling point, amount of volatile organic compounds by weight, and specific gravity for each component of the coating system.
Manufacturer's Instructions	Manufacturer's instructions must include surface preparation details.
Coating Identification	When applicable, the Department will conduct Fourier Transform Infrared Spectroscopy (FTIR) analysis on coating system components for material identification.
Product Sample (for APL listing)	A sample may be requested to verify the product. If the product is a system, a sample of each component must be submitted. Prepare samples in accordance with the product specific requirements of this Section.

ARTICLE 975-6 is deleted and the following substituted:

975-6 Class 5 Applied Finish Coatings.

975-6.1 General: All coatings shall possess physical properties and handling characteristics compatible with the application requirements of Section 400. Unless otherwise specified, the color of the finish coat shall meet SAE Standard AMS-STD-595A, Appendix A – Master Color List, Shade No. 36622, or No. 36642 for uncoated weathering steel bridges. Upon request, submit a one-quart wet sample of each component of each coating system to the SMO.

975-6.2 Textured Finish Coatings: Submit the samples to an independent laboratory for testing. Textured finish coatings shall meet the requirements in Table 975-5.

975-6.3 Water-Repellent Coatings: Submit the samples to an independent laboratory for testing. Water-Repellent coatings shall meet the requirements in Table 975-5 and shall be of water-based silicone acrylic.

Table 975-5 Class 5 Applied Finish Coatings Performance Requirements		
Laboratory Testing		
Property	Test Method	Acceptance Criteria
Resistance to Wind Driven Rain	ASTM D6904	No visible water leaks, and if the rear face of the block is damp, the average gain in weight of the three 8"x16"x2" blocks must be less than 0.2 lb.
Freeze Thaw Resistance	AASHTO R 31 Test No. 6	No disbondment
Water Vapor Transmission	ASTM D1653 Method B Condition C	WVT $\geq$ 10 perms
Abrasion Resistance	ASTM D968, 3,000 Liters of Sand	No loss of coating thickness per ASTM D6132
Salt Spray (Fog) Resistance	ASTM B117 2,000 hours	No disbondment
Fluorescent UV-Condensation Exposure	ASTM D4587 2000 hours 4 hours UV 4 hours Condensation	No blistering per ASTM D714. No cracking or delamination. Chalking rating no less than 8 per ASTM D4214 Method D.
Fungal Resistance	ASTM D3273	Rating of 10 per ASTM D3274